

Title (en)

OPHTHALMIC LENS MOLD SURFACE ENERGY DIFFERENTIAL

Title (de)

OBERFLÄCHENERGIEDIFFERENTIAL EINER FORM FÜR EINE OPHTHALMISCHE LINSE

Title (fr)

DIFFÉRENTIEL D'ÉNERGIE DE SURFACE DE MOULE À LENTILLE OPHTALMIQUE

Publication

EP 2152503 A1 20100217 (EN)

Application

EP 08746429 A 20080421

Priority

- US 2008061004 W 20080421
- US 91307807 P 20070420
- US 75319807 A 20070524

Abstract (en)

[origin: WO2008131329A1] This invention discloses improved mold parts fashioned from a thermoplastic resin compounded with an additive to reduce the surface energy of the mold part (to below 30 mN/m). The mold parts can be used in manufacturing processes, such as, for example: continuous, in-line or batched processes of ophthalmic lens molds.

IPC 8 full level

B29D 11/00 (2006.01)

CPC (source: EP KR)

B29C 33/38 (2013.01 - KR); **B29D 11/00** (2013.01 - KR); **B29D 11/00192** (2013.01 - EP)

Citation (search report)

See references of WO 2008131329A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR

Designated extension state (EPC)

AL BA MK RS

DOCDB simple family (publication)

WO 2008131329 A1 20081030; AR 066116 A1 20090722; AU 2008242679 A1 20081030; BR PI0810237 A2 20141029; CA 2684870 A1 20081030; EP 2152503 A1 20100217; JP 2010524729 A 20100722; KR 20100017185 A 20100216; RU 2009142845 A 20110527; TW 200912424 A 20090316

DOCDB simple family (application)

US 2008061004 W 20080421; AR P080101612 A 20080418; AU 2008242679 A 20080421; BR PI0810237 A 20080421; CA 2684870 A 20080421; EP 08746429 A 20080421; JP 2010504307 A 20080421; KR 20097024210 A 20080421; RU 2009142845 A 20080421; TW 97114043 A 20080418