

Title (en)

ABRASION-RESISTANT STEEL SHEET HAVING EXCELLENT PROCESSABILITY, AND METHOD FOR PRODUCTION THEREOF

Title (de)

ABRIEBFESTES STAHLBLECH MIT HERVORRAGENDER VERARBEITBARKEIT UND HERSTELLUNGSVERFAHREN DAFÜR

Title (fr)

TÔLE D'ACIER RÉSISTANTE À L'ABRASION EXTRÊMEMENT FACILE À METTRE EN UVRE ET SON PROCÉDÉ DE PRODUCTION

Publication

EP 2154262 B1 20180307 (EN)

Application

EP 08764952 A 20080526

Priority

- JP 2008060096 W 20080526
- JP 2007142003 A 20070529
- JP 2008113529 A 20080424

Abstract (en)

[origin: EP2154262A1] An abrasion resistant steel excellent in bending formability and suitable for members, e.g., power shovels, which come into contact with earth and sand, and a production method thereof are provided. Specifically, the steel contains, on a percent by mass basis, 0.05% to 0.35% of C, 0.05% to 1.0% of Si, 0.1% to 2.0% of Mn, 0.1% to 1.2% of Ti, 0.1% or less of Al, at least one element of 0.1% to 1.0% of Cu, 0.1% to 2.0% of Ni, 0.1% to 1.0% of Cr, 0.05% to 1.0% of Mo, 0.05% to 1.0% of W, and 0.0003% to 0.0030% of B, if necessary at least one element of 0.005% to 1.0% of Nb and 0.005% to 1.0% of V, and the remainder including Fe and incidental impurities, where DI^* represented by the following formula is less than 60. $DI^* = 33.85 \times 0.1 \times C^* \times 0.5 \times 0.7 \times Si + 1 \times 3.33 \times Mn + 1 \times 0.35 \times Cu + 1 \times 0.36 \times Ni + 1 \times 2.16 \times Cr + 1 \times 3 \times Mo^* + 1 \times 1.5 \times W^* + 1$ where $C^* = C - 1/4 \times (Ti - 48/14N)$, $Mo^* = Mo \times (1 - 0.5 \times (Ti - 48/14N))$, and $W^* = W \times (1 - 0.5 \times (Ti - 48/14N))$.

IPC 8 full level

C22C 38/58 (2006.01); **C21D 1/06** (2006.01); **C21D 8/02** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01); **C22C 38/14** (2006.01); **C22C 38/22** (2006.01); **C22C 38/28** (2006.01)

CPC (source: EP KR US)

C21D 8/02 (2013.01 - KR); **C21D 8/0226** (2013.01 - EP US); **C21D 8/0263** (2013.01 - EP US); **C22C 38/02** (2013.01 - EP US); **C22C 38/04** (2013.01 - EP US); **C22C 38/14** (2013.01 - EP US); **C22C 38/22** (2013.01 - EP US); **C22C 38/28** (2013.01 - EP US); **C22C 38/58** (2013.01 - KR); **C21D 1/06** (2013.01 - EP US); **C21D 2211/004** (2013.01 - EP US); **C21D 2211/005** (2013.01 - EP US); **C21D 2211/009** (2013.01 - EP US)

Cited by

EP2657361A4; FR2960883A1; AU2011260493B2; EA023196B1; US10662493B2; US9273383B2; WO2011151186A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR

DOCDB simple family (publication)

EP 2154262 A1 20100217; **EP 2154262 A4 20160120**; **EP 2154262 B1 20180307**; AU 2008255706 A1 20081204; AU 2008255706 B2 20111013; BR PI0812277 A2 20141118; CA 2685710 A1 20081204; CA 2685710 C 20120731; CL 2008001542 A1 20080905; CN 101688283 A 20100331; CN 101688283 B 20120201; JP 2009007665 A 20090115; JP 5380892 B2 20140108; KR 101165654 B1 20120716; KR 20090123006 A 20091201; MX 2009012820 A 20091215; PE 20090342 A1 20090329; US 2010147424 A1 20100617; WO 2008146929 A1 20081204; WO 2008146929 A9 20091112

DOCDB simple family (application)

EP 08764952 A 20080526; AU 2008255706 A 20080526; BR PI0812277 A 20080526; CA 2685710 A 20080526; CL 2008001542 A 20080528; CN 200880016192 A 20080526; JP 2008060096 W 20080526; JP 2008113529 A 20080424; KR 20097021902 A 20080526; MX 2009012820 A 20080526; PE 2008000905 A 20080528; US 60089108 A 20080526