

Title (en)

METHOD FOR PRODUCING A SURFACE-DECARBONIZED HOT-ROLLED STRIP

Title (de)

VERFAHREN ZUM HERSTELLEN EINES OBERFLÄCHENENTKOHLTEN WARMBANDS

Title (fr)

PROCÉDÉ DE FABRICATION D'UN FEUILLARD À CHAUD DÉCARBURÉ EN SURFACE

Publication

EP 2179066 B1 20130501 (DE)

Application

EP 08786978 A 20080807

Priority

- EP 2008060378 W 20080807
- DE 102007039013 A 20070817

Abstract (en)

[origin: DE102007039013B3] The production process involves creating the strip from heat-treated steel, heating it while wound as an open coil within austenitizing temperature limits, keeping it incandescent in a carbon-free atmosphere for at least 90 minutes, in which the atmosphere absorbs carbon from the steel, and cooling at an accelerated rate.

IPC 8 full level

C21D 1/74 (2006.01); **C21D 3/04** (2006.01); **C21D 8/02** (2006.01)

CPC (source: EP US)

C21D 1/74 (2013.01 - EP US); **C21D 3/04** (2013.01 - EP US); **C21D 8/0257** (2013.01 - EP US); **C21D 9/46** (2013.01 - EP US); **C21D 9/48** (2013.01 - EP US); **C22C 38/02** (2013.01 - EP US); **C22C 38/04** (2013.01 - EP US); **C22C 38/06** (2013.01 - EP US); **C22C 38/40** (2013.01 - EP US)

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR

DOCDB simple family (publication)

DE 102007039013 B3 20080814; CN 101802232 A 20100811; CN 101802232 B 20120704; EP 2179066 A1 20100428; EP 2179066 B1 20130501; ES 2422738 T3 20130913; JP 2010537045 A 20101202; JP 5599708 B2 20141001; PL 2179066 T3 20130930; US 2010319812 A1 20101223; US 8449694 B2 20130528; WO 2009024472 A1 20090226

DOCDB simple family (application)

DE 102007039013 A 20070817; CN 200880103385 A 20080807; EP 08786978 A 20080807; EP 2008060378 W 20080807; ES 08786978 T 20080807; JP 2010521385 A 20080807; PL 08786978 T 20080807; US 67366408 A 20080807