

## Title (en)

Method for manufacturing wood fibre substances and wood fibre substances with lower emissions of volatile VOC

## Title (de)

Verfahren zur Herstellung von Holzfaserverwerkstoffen sowie Holzfaserverwerkstoffe mit verringerter Emission an flüchtigen VOC

## Title (fr)

Procédé de fabrication de matières premières en fibres de bois et matières premières en fibres de bois ayant des émissions réduites en VOC volatiles

## Publication

**EP 2181818 A2 20100505 (DE)**

## Application

**EP 09174396 A 20091028**

## Priority

DE 102008056280 A 20081028

## Abstract (en)

Producing wood fiber materials with reduced emission of volatile organic compounds comprises chopping wood, cleaning, plasticizing the chopped wood under pressure and temperature and fraying in a refiner and coating and pressing wood fibers, where unchopped and/or chopped wood is contacted with a formulation containing a compound for adjusting neutral to alkaline pH value comprising e.g. alkali- and alkaline earth-carbonates, and a complexing agent comprising e.g. polyvalent and polyfunctional carboxylic acids aminomethyl carboxylic acids and aminomethyl phosphonic acids. Producing wood fiber materials with reduced emission of volatile organic compounds comprises chopping wood, cleaning, plasticizing the chopped wood under pressure and temperature and fraying in a refiner and coating and pressing wood fibers, where unchopped and/or chopped wood is contacted with a formulation containing at least a compound for adjusting neutral to alkaline pH value comprising alkali- and alkaline earth-carbonates, -phosphates, -dihydrogen phosphates, -hydrogen phosphates, -oxides, -hydroxides, or -silicates, and at least a complexing agent comprising polyvalent and polyfunctional carboxylic acids, aminomethyl carboxylic acids, aminomethyl phosphonic acids, ethylenediaminetetraacetic acid, diethylene triamine pentaacetic acid, ethylene glycol tetraacetic acid, ethylenediamine-N,N'-disuccinic acid or its salts, polyphenols, tannins, amino acids, peptides, proteins, polycarboxylates, phosphates, polyphosphates, phosphonic acids, polyphosphonates, or phosphorylated, sulfated or sulfonated polymers. An independent claim is included for a wood fiber material made of plasticized fatty acid ester containing wood or wood particles, where: the wood fiber material exhibits no off-odor caused by furfural and degradation products of fatty acid esters and fatty acids, such as propanal, hexanal, nonanal, 2-octenal, 2-heptenal, 2-decenal, octanal, propionic acid, butyric acid or hexanoic acid; the wood fiber material, after 28 days test period under committee for the health-related evaluation of building products- or Natureplus(RTM: Eco-friendly volatile organic compound-free inks support for protecting nature, earth and health)-test conditions, no unsaturated aldehydes from the reduction of fatty acid esters and fatty acids at a concentration of greater than 5  $\mu\text{g}/\text{m}^3$ , and no furfural at a concentration of greater than 10  $\mu\text{g}/\text{m}^3$  are emitted and exhibits total emission of aldehydes, which lies at below 20  $\mu\text{g}/\text{m}^3$ ; and the wood fiber material contains a complexing agent at a concentration of at least 0.1  $\text{mg}/\text{g}$ .

## Abstract (de)

Die Erfindung betrifft Verfahren zur Herstellung von Holzfaserverwerkstoffen sowie Holzfaserverwerkstoffe aus Holzfasern, welche nach Plastifizierung von Holz gewonnen werden und die eine verringerte Emission an flüchtigen organischen Verbindungen (VOC), insbesondere aliphatische und aromatische Aldehyde, insbesondere Hexanal und Furfural aufweisen. Die Holzfaserverwerkstoffen mit verringerter Emission an flüchtigen organischen Verbindungen (VOC), bei denen Holz zerkleinert, gereinigt, das so zerkleinerte Holz unter Druck und Temperatur plastifiziert und im Refiner zerfasert wird und anschließend die Holzfasern beleimt und verpresst werden, werden so hergestellt, dass das unzerkleinerte und/oder das zerkleinerte Holz mit einer Formulierung, die mindestens eine Verbindung zur Einstellung eines neutralen bis basischen pH-Wertes und mindestens einen Komplexbildner enthält, kontaktiert wird, wobei die Verbindungen zur Einstellung eines neutralen bis basischen pH-Wertes ausgewählt sind aus Alkali- und Erdalkalibicarbonaten, Alkali- und Erdalkalibicarbonaten, -phosphaten, -dihydrogenphosphaten, -hydrogenphosphaten, -oxiden, -hydroxiden, und -silikaten und wobei die Komplexbildner ausgewählt sind aus mehrwertigen und polyfunktionellen Carbonsäuren, Aminomethylcarbonsäuren, Aminomethylphosphonsäuren und deren Verbindungen, EDTA, DTPA EGTA, EDDS und deren Salzen, Polyphenolen, Tanninen, Aminosäuren, Peptiden, Proteinen, Polycarboxylaten, Phosphaten, Polyphosphaten, Phosphonsäuren, Polyphosphonaten, phosphatierten, phosphorylierten, sulfatierten und sulfonierten Polymeren.

## IPC 8 full level

**B27N 1/00** (2006.01)

## CPC (source: EP)

**B27N 1/003** (2013.01)

## Cited by

EP2974841A1; EP2546038A1; DE102014114921A1; DE102011104025A1; DE102012020842A1; WO2014064209A1

## Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

## Designated extension state (EPC)

AL BA RS

## DOCDB simple family (publication)

**EP 2181818 A2 20100505; EP 2181818 A3 20120822; DE 102009046127 A1 20100429**

## DOCDB simple family (application)

**EP 09174396 A 20091028; DE 102009046127 A 20091028**