

Title (en)  
USE OF A DUPLEX STAINLESS STEEL IN A PHOSPHORIC ACID PRODUCTION SYSTEM

Title (de)  
VERWENDUNG EINES ROSTFREIEN DUPLEXSTAHL IN EINEM SYSTEM ZUR HERSTELLUNG VON PHOSPHORSÄURE

Title (fr)  
UTILISATION D'UN ACIER INOXYDABLE DUPLEX DANS UN SYSTÈME DE PRODUCTION D'ACIDE PHOSPHORIQUE

Publication  
**EP 2215421 A1 20100811 (EN)**

Application  
**EP 08841210 A 20081024**

Priority  
• SE 2008051204 W 20081024  
• SE 0702392 A 20071026

Abstract (en)  
[origin: WO2009054799A1] The present disclosure relates to the use of a duplex stainless steel as heat exchanger material in a phosphoric acid production system using the wet method. The steel has the following composition in percent by weight : C max 0.03 Si max 0.5 Mn max 3 Cr 26-29 Ni 4.9-10 Mo 3-5 N 0.35-0.5 B max 0.0030 Co max 3.5 W max 3 Cu max 2 Ru max 0.3 balance Fe and normal occurring impurities.

IPC 8 full level  
**F28F 21/08** (2006.01); **C01B 25/22** (2006.01); **C01B 25/234** (2006.01); **C22C 38/40** (2006.01); **C22C 38/42** (2006.01); **C22C 38/44** (2006.01); **C22C 38/52** (2006.01); **C22C 38/54** (2006.01); **C22C 38/58** (2006.01)

CPC (source: EP SE US)  
**C22C 38/001** (2013.01 - EP US); **C22C 38/42** (2013.01 - SE); **C22C 38/44** (2013.01 - SE); **C22C 38/52** (2013.01 - SE); **C22C 38/54** (2013.01 - SE); **C22C 38/58** (2013.01 - SE); **F28F 21/08** (2013.01 - SE); **F28F 21/083** (2013.01 - EP US)

Designated contracting state (EPC)  
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR

Designated extension state (EPC)  
AL BA MK RS

DOCDB simple family (publication)  
**WO 2009054799 A1 20090430**; EP 2215421 A1 20100811; EP 2215421 A4 20101006; SE 0702392 L 20090427; SE 531593 C2 20090602; US 2010294472 A1 20101125

DOCDB simple family (application)  
**SE 2008051204 W 20081024**; EP 08841210 A 20081024; SE 0702392 A 20071026; US 73959308 A 20081024