

Title (en)
STABLE AQUEOUS SLURRY SUSPENSIONS

Title (de)
STABILE WÄSSRIGE AUFSCHLÄMMUNGSSUSPENSIONEN

Title (fr)
SUSPENSIONS EN BOUILLIE AQUEUSES STABLES

Publication
EP 2268777 A4 20111123 (EN)

Application
EP 08743223 A 20080424

Priority
US 2008005256 W 20080424

Abstract (en)
[origin: WO2009131556A1] An aqueous slurry composition for lapping, saw wire cutting, and finishing operations which contains about 0.1 to 70% by weight of abrasive particles, 0.1 to 20% by weight of suspending particles that have a density of less than or similar to the aqueous or semi-aqueous carrier medium, and the method for creating the suspension.

IPC 8 full level
C09G 1/02 (2006.01); **C09K 3/14** (2006.01); **C10M 103/06** (2006.01)

CPC (source: EP)
C09G 1/02 (2013.01); **C09K 3/1463** (2013.01); **C10M 173/02** (2013.01); **C10M 2201/061** (2013.01); **C10M 2201/062** (2013.01); **C10M 2201/084** (2013.01); **C10M 2207/0406** (2013.01); **C10M 2207/046** (2013.01); **C10M 2215/04** (2013.01); **C10N 2040/22** (2013.01); **C10N 2050/015** (2020.05)

Citation (search report)

- [X] US 2002128327 A1 20020912 - ISHITOBI KEN [JP], et al
- [X] DATABASE WPI Week 198329, Derwent World Patents Index; AN 1983-715136, XP002661480
- See references of WO 2009131556A1

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR

DOCDB simple family (publication)
WO 2009131556 A1 20091029; CN 102027101 A 20110420; EP 2268777 A1 20110105; EP 2268777 A4 20111123; JP 2011524814 A 20110908; JP 5539321 B2 20140702; KR 20110013417 A 20110209

DOCDB simple family (application)
US 2008005256 W 20080424; CN 200880128787 A 20080424; EP 08743223 A 20080424; JP 2011506239 A 20080424; KR 20107026288 A 20080424