

Title (en)
MODIFYING COMPOSITION FOR ASPHALT-CONCRETE MIXTURES

Title (de)
MODIFIZIERUNGSZUSAMMENSETZUNG FÜR ASPHALT-BETON-MISCHUNGEN

Title (fr)
COMPOSITION MODIFIANTE POUR MÉLANGES DE BÉTON ET D'ASPHALTE

Publication
EP 2301996 A4 20110907 (EN)

Application
EP 08873591 A 20080324

Priority
RU 2008000171 W 20080324

Abstract (en)
[origin: EP2301996A1] The inventions relate to the field of road-building materials and the process of their production and can be applied to building of road surface, bridges, airfields, and hydraulic structures. The object of the invention is to develop the modifying composition for various types of road concrete mixes, said composition being introduced into the road concrete mix directly during the preparation of said mix, which enhance the performance of various types of asphalt concretes on the basis of these mixes. Another object of the invention is to provide a process for preparation of modified asphalt concrete mixes. The modifying composition comprises the active rubber powder with the particle size no more than 0.8mm and the specific surface area no less than 0.5m²/g produced through the thermomechanical pulverization of vulcanized rubber in the presence of antiagglomerator, selected from the group consisting of paraffin, ozokerite, and halogenated alcohol-telomers in amounts of 0.1-2% of the weight of vulcanized rubber. The composition comprises additionally metasilicate of a needle-shaped structure, the initiator of gelation selected from the group including 4-nitro-N-methylamine, N-methyl-N, 4-dinitrosoaniline, N-(2-methyl-2-nitropropyl)-4-nitrosoaniline, N-nitrosodiphenylamine, and at least one structurizing agent with the increased induction period of structurization selected from the group, including oligomeric epoxy ether resin, epoxy resin with reactive end groups, and polycondensation resin promoting the formation of branched or network structures, with the following component ratio, wt. %: active rubber powder 65-90; metasilicate of a needle-shaped structure 4.0-25.0; initiator of gelation 1.0-4.5; structurizing agent or structurizing agents 1.7-6.0. The process for the preparation of the modified road concrete mix is accomplished by blending the constituents of the mineral component of a road concrete mix, namely, crushed stone, sand, and mineral powder at a temperature of 140-150°C, with the subsequent addition of a bitumen heated up to 140-150°C. Simultaneously with the bitumen's addition or immediately after it said modifying composition is introduced at a temperature of 150-180°C in amounts of 0.32-3.5 wt. % of the weight of the mineral component of a road concrete mix.

IPC 8 full level
C08L 17/00 (2006.01); **C04B 26/26** (2006.01); **C08J 11/06** (2006.01); **C08L 95/00** (2006.01)

CPC (source: EP)
C04B 26/26 (2013.01); **C08K 3/34** (2013.01); **C08L 19/003** (2013.01); **C08L 95/00** (2013.01); **C04B 2111/0075** (2013.01); **Y02W 30/91** (2015.05)

Citation (search report)

- [A] WO 9221820 A1 19921210 - CAUSYN DAVID W [CA], et al
- [A] EP 1362681 A1 20031119 - CHEMPLAST GMBH [DE], et al
- [A] US 6235809 B1 20010522 - DILULLO ARIAS GINO F [VE], et al
- [A] US 5558704 A 19960924 - MASUDA KINJI [JP], et al
- [A] US 6444731 B1 20020903 - MEMON G MOHAMMED [US]
- See references of WO 2009120104A1

Cited by
CN110790535A; EP3797138A4; CN110922098A; WO2019224808A1

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR

DOCDB simple family (publication)
EP 2301996 A1 20110330; EP 2301996 A4 20110907; DE 08873591 T1 20120126; EA 019389 B1 20140331; EA 201001076 A1 20110228; WO 2009120104 A1 20091001

DOCDB simple family (application)
EP 08873591 A 20080324; DE 08873591 T 20080324; EA 201001076 A 20080324; RU 2008000171 W 20080324