

Title (en)

METHOD FOR PRODUCING AN IMPROVED ELECTRICAL STEEL STRIP

Title (de)

VERFAHREN ZUM HERSTELLEN EINES VERBESSERTEN ELEKTROBANDES

Title (fr)

PROCÉDÉ DE FABRICATION D'UN FEUILLARD MAGNÉTIQUE AMÉLIORÉ

Publication

**EP 2356263 B1 20130522 (DE)**

Application

**EP 09756690 A 20091023**

Priority

- EP 2009063964 W 20091023
- DE 102008061983 A 20081212

Abstract (en)

[origin: WO2010066497A1] The invention relates to a method for producing an electrical steel strip, particularly an iron oxide coated steel strip for use as magnetic steel sheet for the electronics industry, wherein the steel plate strip is fed to a sealed treatment chamber in a continuous process, wherein the electrical steel strip is introduced into the treatment chamber at a temperature of 450°C to 550°C and there loaded with compressed air and an oxygen concentration between 0.05% and 0.2% oxygen, measured in the total furnace space atmosphere, wherein the dew point of water is adjusted to below -100°C and the furnace space atmosphere is reducing. The invention also relates to the electrical plate and to the use thereof.

IPC 8 full level

**C21D 8/12** (2006.01)

CPC (source: EP KR US)

**C21D 8/12** (2013.01 - KR); **C21D 8/1272** (2013.01 - EP US); **C21D 8/1277** (2013.01 - EP US); **C21D 8/1283** (2013.01 - EP US);  
**Y10T 156/10** (2015.01 - EP US)

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

DOCDB simple family (publication)

**DE 102008061983 A1 20100617; DE 102008061983 B4 20111208;** BR PI0916493 A2 20160216; EP 2356263 A1 20110817;  
EP 2356263 B1 20130522; JP 2012511628 A 20120524; KR 20110111404 A 20111011; PL 2356263 T3 20131031; RU 2011128544 A 20130120;  
RU 2499845 C2 20131127; SI 2356263 T1 20130930; US 2011297292 A1 20111208; WO 2010066497 A1 20100617

DOCDB simple family (application)

**DE 102008061983 A 20081212;** BR PI0916493 A 20091023; EP 09756690 A 20091023; EP 2009063964 W 20091023;  
JP 2011539980 A 20091023; KR 20117016179 A 20091023; PL 09756690 T 20091023; RU 2011128544 A 20091023; SI 200930672 T 20091023;  
US 200913139282 A 20091023