

Title (en)
SPHEROIDAL GRAPHITE CAST IRON

Title (de)
KUGELGRAPHIT-GUSSEISEN

Title (fr)
FONTE À GRAPHITE SPHÉROÏDAL

Publication
EP 2377960 A4 20161214 (EN)

Application
EP 09833255 A 20090730

Priority
• JP 2008322696 A 20081218
• JP 2009063560 W 20090730

Abstract (en)
[origin: US2011211986A1] A ductile iron having superior high-temperature strength and oxidation resistance at temperatures exceeding 800° C. compared with conventional high Si and Mo ductile iron. The ductile iron comprises, in terms of mass ratio, carbon: 2.0 to 4.0%, silicon: 3.5 to 5.0%, manganese: not more than 1.0%, chromium: 0.1 to 1.0%, molybdenum: 0.2 to 2.0%, vanadium: 0.1 to 1.0%, and magnesium: 0.02 to 0.1%, with the remainder being composed of iron and unavoidable impurities.

IPC 8 full level
C22C 37/04 (2006.01); **C22C 37/06** (2006.01); **C22C 37/10** (2006.01)

CPC (source: EP KR US)
C21D 5/00 (2013.01 - EP US); **C22C 37/04** (2013.01 - EP KR US); **C22C 37/06** (2013.01 - EP US); **C22C 37/10** (2013.01 - EP US)

Citation (search report)
• [A] WO 2008112720 A1 20080918 - WESCAST IND INC [CA], et al
• See references of WO 2010070949A1

Cited by
EP3118340A4; US10294550B2

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

DOCDB simple family (publication)
US 2011211986 A1 20110901; CN 102264931 A 20111130; CN 102264931 B 20140903; EP 2377960 A1 20111019; EP 2377960 A4 20161214; EP 2377960 B1 20180926; EP 2377960 B2 20220406; JP 2010144216 A 20100701; JP 5232620 B2 20130710; KR 101373488 B1 20140312; KR 20110069170 A 20110622; WO 2010070949 A1 20100624

DOCDB simple family (application)
US 200913127403 A 20090730; CN 200980146974 A 20090730; EP 09833255 A 20090730; JP 2008322696 A 20081218; JP 2009063560 W 20090730; KR 20117010779 A 20090730