

Title (en)

Process for producing a single-crystal component made of a nickel-based superalloy

Title (de)

Verfahren zur Herstellung einer aus einer Nickel-Basis-Superlegierung bestehenden Einkristallkomponente

Title (fr)

Procédé de fabrication d'un composant monocristallin constitué d'un superalliage à base de nickel

Publication

EP 2402473 B1 20170426 (DE)

Application

EP 11171088 A 20110622

Priority

CH 10582010 A 20100630

Abstract (en)

[origin: EP2402473A2] Producing a single-crystal component comprising a nickel-based superalloy or a directionally solidified component, comprises casting the component in a known manner, solution annealing for homogenization of the cast structure of the component, and carrying out two-step precipitation heat treatment comprising (a) determining a dendrite arm spacing in different areas of the cast component, (b) identifying a slowest diffusion element in the superalloy, (c) calculating the required time (t), (d) solution annealing the cast component, and (e) carrying out a two-step precipitation treatment. Producing a single-crystal component comprising a nickel-based superalloy or a directionally solidified component, comprises casting the component in a known manner to form a structure exhibiting dendrite, solution annealing for homogenization of the cast structure of the component, and carrying out a two-step precipitation heat treatment comprising (a) determining a dendrite arm spacing in different areas of the cast component, (b) identifying a slowest diffusion element in the composition of the respective nickel-based superalloy for determining the diffusion coefficients, (c) calculating the required time (t), which is necessary to ensure the segregation of the slowest element diffusion at #5% to reduce to a solution annealing temperature (T1), which on one hand is lower than the starting melt temperature, and on the other hand is high enough to lie in the required heat treatment window, (d) solution annealing the cast component comprising heating the component to the solution annealing temperature (T1), holding at this temperature (T1) with calculated time (t) in the step (c), and quenching the temperature (T1) at room temperature with a rate (v1) of #50[deg] C/minute, (e) carrying out the two-step precipitation treatment for separating the #'-phase at respectively lower temperatures (T2) and (T3) following the step (d), where the first step of the precipitation treatment comprises carrying out hot isostatic pressing process with an isostatic pressure greater than 160 MPa at the holding temperature (T2) and subsequent cooling of the temperature (T2) to room temperature with a cooling rate (v2) of greater than 50[deg] C/minutes, and the subsequent second step of the precipitation treatment comprises heat treatment of the component at a holding temperature (T3) and a subsequent cooling of the temperature (T2) to room temperature with a cooling rate (v3) of 10-50[deg] C/minute.

IPC 8 full level

C22F 1/10 (2006.01); **C22C 19/05** (2006.01); **C30B 33/02** (2006.01)

CPC (source: EP US)

C22C 1/02 (2013.01 - EP US); **C22F 1/10** (2013.01 - EP US)

Cited by

CN110760770A; EP3211111A3; CN105689719A; FR3121453A1; WO2022208004A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)

EP 2402473 A2 20120104; **EP 2402473 A3 20131030**; **EP 2402473 B1 20170426**; **EP 2402473 B8 20170726**; CH 703386 A1 20111230; JP 2012012705 A 20120119; JP 5787643 B2 20150930; US 2012000577 A1 20120105; US 8435362 B2 20130507

DOCDB simple family (application)

EP 11171088 A 20110622; CH 10582010 A 20100630; JP 2011145691 A 20110630; US 201113170570 A 20110628