

Title (en)
FREE-MACHINING AA 6XXX ALUMINUM ALLOY

Title (de)
AUTOMATEN-ALUMINIUM-AA 6XXX LEGIERUNG

Title (fr)
ALLIAGE D'ALUMINIUM DE DÉCOLLETAGE DE LA SÉRIE AA 6XXX

Publication
EP 2421996 A1 20120229 (FR)

Application
EP 10716375 A 20100326

Priority
• FR 2010000262 W 20100326
• FR 0901631 A 20090403

Abstract (en)
[origin: WO2010112698A1] The subject of the invention is an extruded product, of the bar or rod or tube type, with very good precision-turning properties, made of a wrought precision-turning aluminium alloy of the following composition: 0.8 < Si < 1.5%, preferably 1.0 = Si < 1.5%; 1.0 < Fe < 1.8%, preferably 1.0 < Fe = 1.5%; Cu: < 0.1%; Mn: < 1%, preferably < 0.6%; Mg: 0.6 - 1.2%, preferably 0.6 - 0.9%; Ni: < 3.0%, preferably 1.0 - 2.0%; Cr: < 0.25%; Ti: < 0.1%; other elements < 0.05% each and 0.15% in total; and the balance aluminium. The subject of the invention is also a precision-turned part obtained from the extruded product as defined above.

IPC 8 full level
C22C 21/02 (2006.01); **C22C 21/06** (2006.01); **C22C 21/08** (2006.01); **C22F 1/05** (2006.01)

CPC (source: EP US)
C22C 21/02 (2013.01 - EP US); **C22C 21/06** (2013.01 - EP US); **C22C 21/08** (2013.01 - EP US); **C22F 1/05** (2013.01 - EP US)

Citation (search report)
See references of WO 2010112698A1

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

DOCDB simple family (publication)
WO 2010112698 A1 20101007; EP 2421996 A1 20120229; EP 2421996 B1 20180822; ES 2695906 T3 20190111; FR 2944029 A1 20101008; FR 2944029 B1 20110422; RU 2011144509 A 20130510; RU 2522413 C2 20140710; US 2012121456 A1 20120517

DOCDB simple family (application)
FR 2010000262 W 20100326; EP 10716375 A 20100326; ES 10716375 T 20100326; FR 0901631 A 20090403; RU 2011144509 A 20100326; US 201013376871 A 20100326