

Title (en)

Electrode for producing chlorine through electrolysis

Title (de)

Elektrode für die elektrolytische Chlorherstellung

Title (fr)

Electrode pour la production électrolytique de chlore

Publication

**EP 2447395 A2 20120502 (DE)**

Application

**EP 11186428 A 20111025**

Priority

DE 102010043085 A 20101028

Abstract (en)

Electrode comprises at least an electrically conductive substrate and a catalytically active coating. The catalytically active layer is based on two catalytically active components comprising at least iridium, ruthenium or titanium as a metal oxide and/or mixed oxide. The total amount of ruthenium and/or iridium based on the sum of iridium, ruthenium and titanium is at least 10 mole-%, preferably 10-20 mol% and up to half of the ruthenium and/or iridium is replaced by vanadium or zirconium. At least one oxide base layer is applied on the electrically conducting substrate. Electrode comprises at least an electrically conductive substrate and a catalytically active coating. The catalytically active layer is based on two catalytically active components comprising at least iridium, ruthenium or titanium as a metal oxide and/or mixed oxide. The total amount of ruthenium and/or iridium based on the sum of iridium, ruthenium and titanium is at least 10 mole-%, preferably 10-20 mol% and up to half of the ruthenium and/or iridium is replaced by vanadium or zirconium, preferably vanadium. At least one oxide base layer is applied on the electrically conducting substrate and the oxide base layer is impermeable for aqueous electrolytes comprising sodium chloride and/or sodium hydroxide or hydrogen chloride. Independent claims are also included for: (1) producing the electrode, comprising applying sol-gel coating solution containing a solution or dispersion of metal compounds of at least one of ruthenium, iridium or titanium on the electrically conductive substrate, preferably by immersion, removing the solvent, and calcining the dried metal compound layer at elevated temperature, preferably at least 350[deg] C, preferably at least 400[deg] C in the presence of oxygen-containing gases and optionally the steps of applying the solution or dispersion, drying and calcinating is carried out once or repeated many times; and (2) an electrolyzer for electrolyzing the electrolysis of sodium chloride or hydrogen chloride-containing solutions, comprising the electrode as an anode.

Abstract (de)

Es wird eine Elektrode mindestens bestehend aus einem elektrisch leitenden Substrat und einer katalytisch aktiven Beschichtung beschrieben, bei der die katalytische aktive Schicht auf zwei katalytisch aktiven Komponenten basiert, die mindestens Iridium, Ruthenium oder Titan als Metalloxid oder Mischoxid oder Mischungen der genannten Oxide enthält, wobei der Gesamtgehalt an Ruthenium bezogen auf die Summe der Elemente Iridium, Ruthenium und Titan, 10 bis 28 Mol-% beträgt, und dass mindestens eine Basisschicht vorgesehen ist, die auf dem elektrisch leitenden Träger aufgebracht ist und die für wässrige Elektrolyte undurchlässig ist.

IPC 8 full level

**C25B 1/26** (2006.01); **C25B 11/04** (2006.01)

CPC (source: EP US)

**C25B 1/26** (2013.01 - EP US); **C25B 11/093** (2021.01 - EP US)

Citation (applicant)

- US 3632498 A 19720104 - BEER HENRI BERNARD
- US 3562008 A 19710209 - MARTINSONS ALEKSANDRS
- DE 4032417 A1 19920416 - UNIV HALLE WITTENBERG [DE]
- EP 0867527 A1 19980930 - ARAGONESAS IND Y EN S A [ES]
- US 4517068 A 19850514 - HINDEN JEAN M [CH], et al
- WO 2006028443 A1 20060316 - ELTECH SYSTEMS CORP [US], et al
- EP 0046449 A1 19820224 - DIAMOND SHAMROCK CORP [US]
- US 3882002 A 19750506 - COOK JR EDWARD H
- US 3950240 A 19760413 - COOKFAIR ARTHUR S, et al
- US 7211177 B2 20070501 - GESTERMANN FRITZ [DE], et al
- US 3776834 A 19731204 - O LEARY K
- US 4039409 A 19770802 - LACONI ANTHONY B, et al
- US 3948751 A 19760406 - BIANCHI GIUSEPPE, et al
- US 4668531 A 19870526 - ASANO HIROSHI [JP], et al
- WO 2008046784 A1 20080424 - INDUSTRIE DE NORA SPA [IT], et al
- CN 1900368 A 20070124 - UNIV FUZHOU [CN]
- T.A.F. LASSALI ET AL., ELECTROCHIMICA ACTA, vol. 39, 1994, pages 1545
- J. ELECTROCHEM. SOC., vol. 129, 1982, pages 1689
- ELECTROCHIMICA ACTA, vol. 42, 1997, pages 3525
- J. ALLOYS AND COMPOUNDS, vol. 261, 1997, pages 176
- S. TRASATTI, ELECTROCHIM. ACTA, vol. 36, 1991, pages 225
- G.R.P. MALPASS ET AL., ELECTROCHIM. ACTA, vol. 52, 2006, pages 936
- L.M. DA SILVA ET AL., J. ELECTROANAL. CHEM., vol. 532, 2002, pages 141
- TITAN, HAYFIELD, PRECIOUS METAL REVIEW, vol. 27, no. 1, 1983, pages 2 - 8
- Y. TAKASU, ELECTROCHEMICA ACTA, vol. 45, 2000, pages 4135
- S.V. EVDOKIMOV ET AL., RUSSIAN JOURNAL OF ELECTROCHEMISTRY, vol. 38, 2002, pages 657
- Y. E. ROGINSKAYA ET AL., ELECTROCHIMICA ACTA, vol. 40, 1995, pages 817
- V. V. PANIC ET AL., COLLOIDS AND SURFACES A, vol. 157, 1999, pages 269
- Y. ZENG ET AL., CERAMICS INTERNATIONAL, vol. 33, 2007, pages 1087

Cited by

CN111994967A; EP3416222A4; US11069901B2; DE102017214810A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

**EP 2447395 A2 20120502; EP 2447395 A3 20130130;** CN 102465312 A 20120523; DE 102010043085 A1 20120503;  
JP 2012092449 A 20120517; US 2012103828 A1 20120503

DOCDB simple family (application)

**EP 11186428 A 20111025;** CN 201110333700 A 20111028; DE 102010043085 A 20101028; JP 2011235871 A 20111027;  
US 201113280564 A 20111025