

Title (en)

POLYCRYSTALLINE MAGNETOCALORIC MATERIALS

Title (de)

POLYKRISTALLINE MAGNETOKALORISCHE MATERIALIEN

Title (fr)

MATÉRIAUX MAGNÉTOCALORIQUES POLYCRYSTALLINS

Publication

**EP 2467858 B1 20150218 (DE)**

Application

**EP 10744924 A 20100817**

Priority

- EP 09168051 A 20090818
- EP 2010061962 W 20100817
- EP 10744924 A 20100817

Abstract (en)

[origin: US2011041513A1] What are described are polycrystalline magnetocaloric materials of the general formula  $Mn_aCobGe_{x}Ax$  with A, B or C  $0 \leq x \leq 0.5$ ,  $0.9 \leq a \leq 1.1$ ,  $0.9 \leq b \leq 1.1$ ,  $0.9 \leq c \leq 1.0$ , where up to 30 mol % of the Mn or Co may be replaced by Fe, Ni, Cr, V or Cu or up to 30 mol % of the Mn, Co or Ge may be replaced by vacancies, in which phases of the orthorhombic TiNiSi structure type and of the hexagonal Ni<sub>2</sub>In structure type are present at a temperature below -40° C.

IPC 8 full level

**H01F 1/01** (2006.01); **C22C 19/07** (2006.01); **C22C 22/00** (2006.01); **C22C 30/00** (2006.01)

CPC (source: EP KR US)

**C22C 19/07** (2013.01 - EP KR US); **C22C 22/00** (2013.01 - EP KR US); **C22C 30/00** (2013.01 - EP KR US); **H01F 1/015** (2013.01 - EP KR US); **H01F 1/017** (2013.01 - EP KR US)

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

DOCDB simple family (publication)

**US 2011041513 A1 20110224**; BR 112012003818 A2 20160322; CA 2771669 A1 20110224; CN 102576587 A 20120711; CN 102576587 B 20151125; EP 2467858 A1 20120627; EP 2467858 B1 20150218; JP 2013502510 A 20130124; JP 5887599 B2 20160316; KR 20120054637 A 20120530; RU 2012110126 A 20130927; TW 201113911 A 20110416; WO 2011020826 A1 20110224

DOCDB simple family (application)

**US 85275010 A 20100809**; BR 112012003818 A 20100817; CA 2771669 A 20100817; CN 201080046164 A 20100817; EP 10744924 A 20100817; EP 2010061962 W 20100817; JP 2012525157 A 20100817; KR 20127006821 A 20100817; RU 2012110126 A 20100817; TW 99126669 A 20100810