

Title (en)
Medium- or high-voltage electrical cable

Title (de)
Mittel- oder Hochspannungsstromkabel

Title (fr)
Câble électrique à moyenne ou haute tension

Publication
EP 2498264 B1 20130807 (FR)

Application
EP 12158597 A 20120308

Priority
FR 1151869 A 20110308

Abstract (en)
[origin: EP2498264A1] The medium or high voltage electric cable (1) comprises an elongated conductive member (2) surrounded by a polymeric layer (3, 4, 5). The polymeric layer is a non-crosslinking layer obtained from a composition including a thermoplastic polymer (50-100 parts by weight) such as monomodal polyolefin having a capillary viscosity (η) of 0.80 Pa.s at 170[deg] C and at 230[deg] C with a shear of 0.1 s⁻¹. A density of the thermoplastic polymer at 23[deg] C is 941 kg/m³, and a melting temperature of the thermoplastic polymer is 130[deg] C. The medium or high voltage electric cable (1) comprises an elongated conductive member (2) surrounded by a polymeric layer (3, 4, 5). The polymeric layer is a non-crosslinking layer obtained from a composition including a thermoplastic polymer (50-100 parts by weight) such as monomodal polyolefin having a capillary viscosity (η) of 0.80 Pa.s at 170[deg] C and at 230[deg] C with a shear of 0.1 s⁻¹. A density of the thermoplastic polymer at 23[deg] C is 941 kg/m³, and a melting temperature of the thermoplastic polymer is 130[deg] C. A ratio of weight average molecular weight of the thermoplastic polymer and number average molecular weight of the thermoplastic polymer is 5-7. A melt flow index of the thermoplastic polymer is 0.1-2 g/10 minutes. The layers are crosslinked layers, which are electrically insulating layers.

IPC 8 full level
H01B 7/29 (2006.01)

CPC (source: EP)
H01B 7/292 (2013.01)

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)
EP 2498264 A1 20120912; EP 2498264 B1 20130807; ES 2429505 T3 20131115; FR 2972561 A1 20120914

DOCDB simple family (application)
EP 12158597 A 20120308; ES 12158597 T 20120308; FR 1151869 A 20110308