

Title (en)
HIGH STRENGTH STEEL SHEET HAVING EXCELLENT RESISTANCE TO POST WELD HEAT TREATMENT AND METHOD FOR MANUFACTURING SAME

Title (de)
HOCHFESTES STAHLBLECH MIT AUSGEZEICHNETER RESISTENZ GEGEN EINE NACH DEM SCHWEISSEN ERFOLGENDE WÄRMEBEHANDLUNG SOWIE VERFAHREN ZU DESSEN HERSTELLUNG

Title (fr)
FEUILLARD D'ACIER À RÉSISTANCE MÉCANIQUE ÉLEVÉE AYANT UNE EXCELLENTE RÉSISTANCE AU TRAITEMENT THERMIQUE POST-SOUDAGE ET SON PROCÉDÉ DE FABRICATION

Publication
EP 2520680 A4 20141119 (EN)

Application
EP 10841182 A 20101222

Priority
• KR 20090132129 A 20091228
• KR 2010009225 W 20101222

Abstract (en)
[origin: EP2520680A2] Provided are a steel sheet having excellent Post Weld Heat Treatment (PWHT) resistance of which strength and toughness are not deteriorated even after performing PWHT for a lengthy period of time, and a method for manufacturing the steel sheet. The steel sheet has a composition comprising by weight percent: 0.1 to 0.3% of C; 0.15 to 0.50% of Si; 0.6 to 1.2% of Mn; 0.035% or less of P; 0.020% or less of S; 0.001 to 0.05% of Al; 0.01 to 0.35% of Cr; 0.005 to 0.2% of Mo; 0.005 to 0.05% of V; 0.001 to 0.05% of Nb; 0.001 to 0.05% of Ti; 0.0005 to 0.005% of Ca; 0.05 to 0.5% of Ni; one or more selected from the group consisting of 0.005 to 0.5% of Cu, 0.005 to 0.2% of Co and 0.005 to 0.2% of W; and Fe as well as unavoidable impurities.

IPC 8 full level
C22C 38/00 (2006.01); **B21B 1/22** (2006.01); **B21B 3/02** (2006.01); **C21D 8/02** (2006.01)

CPC (source: EP KR)
C21D 8/0226 (2013.01 - EP KR); **C22C 38/002** (2013.01 - EP KR); **C22C 38/02** (2013.01 - EP KR); **C22C 38/04** (2013.01 - EP KR); **C22C 38/06** (2013.01 - EP); **C22C 38/44** (2013.01 - EP KR); **C22C 38/46** (2013.01 - EP KR); **C22C 38/48** (2013.01 - EP KR); **C22C 38/50** (2013.01 - EP KR); **C21D 9/50** (2013.01 - EP); **C21D 2211/004** (2013.01 - EP KR); **C21D 2211/005** (2013.01 - EP KR); **C21D 2211/009** (2013.01 - EP KR)

Citation (search report)
• [A] US 2009025839 A1 20090129 - WATANABE YOSHIYUKI [JP], et al
• [A] JP 2009041073 A 20090226 - SUMITOMO METAL IND
• [AP] EP 2258884 A1 20101208 - KOBE STEEL LTD [JP]
• [A] JP H11131177 A 19990518 - NIPPON STEEL CORP
• [A] JP 2006045672 A 20060216 - JFE STEEL KK
• [A] WO 2009119368 A1 20091001 - KOBE STEEL LTD [JP], et al
• See references of WO 2011081350A2

Cited by
JP2014201760A; EP3733904A4; EP3395984A4; EP3561111A4; US11578376B2; US11649515B2; US11634785B2; US11656169B2; US11788951B2

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)
EP 2520680 A2 20121107; EP 2520680 A4 20141119; EP 2520680 B1 20161026; CN 102782169 A 20121114; CN 102782169 B 20141119; JP 2013515861 A 20130509; JP 5657026 B2 20150121; KR 101322067 B1 20131025; KR 20110075630 A 20110706; WO 2011081350 A2 20110707; WO 2011081350 A3 20111117

DOCDB simple family (application)
EP 10841182 A 20101222; CN 201080064894 A 20101222; JP 2012546997 A 20101222; KR 20090132129 A 20091228; KR 2010009225 W 20101222