

Title (en)
COPPER BASED BINDER FOR THE FABRICATION OF DIAMOND TOOLS

Title (de)
BINDEMITTEL AUF KUPFERBASIS ZUR HERSTELLUNG VON DIAMANTWERKZEUGEN

Title (fr)
LIANT À BASE DE CUIVRE POUR LA FABRICATION D'OUTILS DIAMANTÉS

Publication
EP 2542385 A2 20130109 (EN)

Application
EP 11750978 A 20110217

Priority
• RU 2010107315 A 20100301
• RU 2010107314 A 20100301
• RU 2011000087 W 20110217

Abstract (en)
[origin: WO2011108959A2] This invention relates to powder metallurgy, more specifically, to composite material production methods, and can be used for the production of copper base binders for diamond tools used in the construction industry and stone working, including different designs of segment cutting-off abrasive wheels used for highway and runway repairs, refurbishment of metallurgical plants and nuclear power plants, renovation of bridges and other structures, as well as drills and segment cutting-off abrasive wheels for cutting of high-strength reinforced concretes. Binder affects the design of a tool. It is the binder that determines the choice of the casing material and the method of bounding the diamond layer with the case. Physical and mechanical properties of binders determine potential shapes and sizes of abrasive diamond tools. The object of this invention is to provide diamond tool binders having a higher wear resistance without an essential increase in the required sintering temperature, as well as higher hardness, strength and impact toughness. Said object is achieved by adding a copper group metal as the main binder component and an alloying addition in the form of nanopowder. The copper base diamond tool binder of the first embodiment of the invention has the following components in the following ratios, wt.-%: The copper base diamond tool binder of the other embodiment of the invention has the following components in the following ratios, wt.-%: Cu = 30-60 Fe= 20-35 Co=10-15 Sn= 0-10.5 WC = 0-20 alloying addition = 0.01-5. The alloying addition is introduced in the form of 75-150 m²/g specific surface area nanopowder. The copper base diamond tool binder of the other embodiment of the invention has the following components in the following ratios, wt.-%: Cu = 30-60 Fe= 20-35 Co=10-15 Sn= 0-10.5 WC = 0-20 alloying addition = 0.01-5. The alloying addition is introduced in the form of 75-150 m²/g specific surface area nanopowder.

IPC 8 full level
B24D 3/06 (2006.01); **B22F 1/054** (2022.01); **B82B 1/00** (2006.01)

CPC (source: EP KR US)
B22F 1/054 (2022.01 - EP KR US); **B24D 3/06** (2013.01 - EP KR US); **B24D 99/005** (2013.01 - EP US); **B82B 1/00** (2013.01 - KR); **C22C 1/0425** (2013.01 - EP US); **C22C 32/0021** (2013.01 - EP US); **C22C 32/0052** (2013.01 - EP US); **B22F 2999/00** (2013.01 - EP US); **C22C 26/00** (2013.01 - EP US); **C22C 2026/002** (2013.01 - EP US)

Cited by
RU2685917C1

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)
WO 2011108959 A2 20110909; WO 2011108959 A3 20111020; CN 103038025 A 20130410; CN 103038025 B 20141015; EP 2542385 A2 20130109; EP 2542385 A4 20170802; EP 2542385 B1 20180530; KR 101426184 B1 20140806; KR 20130113918 A 20131016; US 2012325049 A1 20121227; US 9156137 B2 20151013

DOCDB simple family (application)
RU 2011000087 W 20110217; CN 201180011937 A 20110217; EP 11750978 A 20110217; KR 20127025608 A 20110217; US 201113582194 A 20110217