

Title (en)

USE OF CELLULAR CONCRETE AGGREGATES AND MANUFACTURING PROCESS

Title (de)

VERWENDUNG VON PORENBETONZUSCHLAGSTOFFEN UND HERSTELLUNGSVERFAHREN

Title (fr)

UTILISATION DE GRANULATS DE BETON CELLULAIRE ET PROCEDE DE FABRICATION

Publication

EP 2595938 A1 20130529 (FR)

Application

EP 11752266 A 20110721

Priority

- FR 1003056 A 20100721
- FR 2011051763 W 20110721

Abstract (en)

[origin: WO2012010804A1] The invention relates to the use of cellular concrete aggregates sized between 2 and 25 mm and having a bulk density in the dry state of between 200 and 600 kg/m³ enabling their agglomeration by a binder for the manufacture of lightweight and insulating concrete or for the manufacture of slabs, screeds, formwork walls or prefabricated parts. It also relates to a process for manufacturing cellular concrete aggregates of at least 2 mm.

IPC 8 full level

C04B 28/04 (2006.01); **C04B 38/08** (2006.01)

CPC (source: EP US)

B02C 23/08 (2013.01 - US); **C04B 20/026** (2013.01 - US); **C04B 28/04** (2013.01 - EP US); **C04B 38/08** (2013.01 - EP US); **C04B 2111/40** (2013.01 - EP US); **C04B 2111/60** (2013.01 - EP US); **Y02W 30/91** (2015.05 - EP US)

Citation (search report)

See references of WO 2012010804A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)

WO 2012010804 A1 20120126; CO 6680614 A2 20130531; CR 20130030 A 20130618; DO P2013000020 A 20130731; EP 2595938 A1 20130529; FR 2962999 A1 20120127; FR 2962999 B1 20130823; GT 201300022 A 20141028; MX 2013000814 A 20131216; MX 353591 B 20180119; NI 201300009 A 20131016; US 2013181366 A1 20130718; US 9120702 B2 20150901

DOCDB simple family (application)

FR 2011051763 W 20110721; CO 13010228 A 20130121; CR 20130030 A 20130122; DO 2013000020 A 20130118; EP 11752266 A 20110721; FR 1003056 A 20100721; GT 201300022 A 20130118; MX 2013000814 A 20110721; NI 201300009 A 20130118; US 201113811194 A 20110721