

Title (en)  
SECONDARY AQUEOUS DISPERSIONS OF BIODEGRADABLE DIBLOCK COPOLYESTERS, PROCESSES FOR PREPARATION THEREOF AND USE THEREOF

Title (de)  
SEKUNDÄRE WÄSSRIGE DISPERSIONEN BIOABBAUBARER DIBLOCKCOPOLYESTER, VERFAHREN ZU IHRER HERSTELLUNG UND IHRE VERWENDUNG

Title (fr)  
DISPERSIONS AQUEUSES SECONDAIRES DE COPOLYESTERS À DEUX BLOCS BIODÉGRADABLES, PROCÉDÉS POUR LEUR PRÉPARATION ET LEUR UTILISATION

Publication  
**EP 2603542 A1 20130619 (DE)**

Application  
**EP 11751574 A 20110812**

Priority  
• EP 10172840 A 20100813  
• EP 2011063950 W 20110812  
• EP 11751574 A 20110812

Abstract (en)  
[origin: EP2418232A1] Stable secondary aqueous suspension comprises at least one of substituted water-insoluble biodegradable aliphatic diblock copolyesters (I) containing a block of an aliphatic polyester and a block of a polyethylene oxide, where the solid content of (I) in the suspension is at least 10 wt.%, the melting point of (I) is 35-70[deg] C and the mass of the polyethylene oxide in (I) is 500-10000 Daltons. Stable secondary aqueous suspension comprises at least one of substituted water-insoluble biodegradable aliphatic diblock copolyesters of formula (Y1-(O-A-O-C(=O)-(CH 2) p-C(=O)) m-(O-(CH 2) 2 n-O-X) (I) containing a block of an aliphatic polyester and a block of a polyethylene oxide, where the solid content of (I) in the suspension is at least 10 wt.%, the melting point of (I) is 35-70[deg] C and the mass of the polyethylene oxide in (I) is 500-10000 Daltons. A : 3-12C alkylene; p : 1-14; m : 10-500; n : 10-500; X : H, alkoxide, 1-20C alkyl or phenyl; and Y1 : H, alkoxide, 1-20C alkyl, carboxylate, carboxylic acid, ester or thioether. Independent claims are also included for: (1) preparing aqueous suspensions stable biodegradable copolyester comprising: dissolving particles of (I) in a polar aprotic solvent; mixing this solution with water and then removing the polar aprotic solvent; and dialyzing the obtained suspension against a water-soluble polymer; (2) use of stable secondary aqueous suspension for the preparation of nano and microfibers, and nano and microfiber nonwovens with random or oriented fibers by electrospinning, where an electrospinning solution is added at a proportion of 2-10 wt.% of a water soluble polymer; and (3) nano- and meso-fibers and nano-and meso-fiber fleeces obtained by electrospinning the secondary aqueous suspension.

IPC 8 full level  
**C08G 63/672** (2006.01); **C08L 67/02** (2006.01); **D01D 5/00** (2006.01); **D01F 6/86** (2006.01)

CPC (source: EP US)  
**C08G 63/672** (2013.01 - EP US); **C08L 67/02** (2013.01 - US); **C08L 67/025** (2013.01 - EP US); **D01D 1/02** (2013.01 - EP US); **D01D 5/0038** (2013.01 - EP US); **D01F 6/62** (2013.01 - EP US); **D01F 6/92** (2013.01 - EP US)

Citation (search report)  
See references of WO 2012020127A1

Designated contracting state (EPC)  
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)  
**EP 2418232 A1 20120215; EP 2418232 B1 20130703**; EP 2603542 A1 20130619; US 2013214441 A1 20130822; WO 2012020127 A1 20120216

DOCDB simple family (application)  
**EP 10172840 A 20100813**; EP 11751574 A 20110812; EP 2011063950 W 20110812; US 201113816701 A 20110812