

Title (en)  
PICKERING EMULSION FOR PRODUCING ELECTRICALLY CONDUCTIVE COATINGS AND PROCESS FOR PRODUCING A PICKERING EMULSION

Title (de)  
PICKERING-EMULSION ZUR HERSTELLUNG ELEKTRISCH LEITFÄHIGER BESCHICHTUNGEN UND VERFAHREN ZUR HERSTELLUNG EINER PICKERING-EMULSION

Title (fr)  
ÉMULSION DE PICKERING POUR LA FABRICATION DE REVÊTEMENTS ÉLECTROCONDUCTEURS ET PROCÉDÉ DE PRÉPARATION D'UNE ÉMULSION DE PICKERING

Publication  
**EP 2655526 A2 20131030 (DE)**

Application  
**EP 11797328 A 20111219**

Priority  
• EP 10196109 A 20101221  
• EP 2011073276 W 20111219  
• EP 11797328 A 20111219

Abstract (en)  
[origin: EP2468826A1] Producing a pickering emulsion for producing conductive coatings, comprises: (a) mixing an aqueous dispersion containing sterically stabilized silver nanoparticles and water with at least one water-immiscible solvent and dispersing into an emulsion, where the content of stabilized silver nanoparticles is 0.5-7 wt.%; (b) separating the emulsion obtained during a residence time in the step (a) into an upper concentrated emulsion phase and a lower aqueous phase by creaming; and (c) isolating the resulting upper concentrated emulsion phase. Producing a pickering emulsion for producing conductive coatings, comprises: (a) mixing an aqueous dispersion containing sterically stabilized silver nanoparticles and water with at least one water-immiscible solvent and dispersing into an emulsion, where the content of stabilized silver nanoparticles is 0.5-7 wt.%; (b) separating the emulsion obtained during a residence time in the step (a) into an upper concentrated emulsion phase and a lower aqueous phase by creaming; and (c) isolating the resulting upper concentrated emulsion phase, where the emulsion phase has a content of silver nanoparticles up to 7 wt.%, preferably up to 4.5 wt.%, based on their total weight. Independent claims are also included for: (1) a pickering emulsion for producing conductive coatings, comprising emulsion stabilized silver nanoparticles, water and at least one organic water-immiscible solvent, where the stabilized silver nanoparticles are present in an amount of 0.5-7 wt.%, based on the total weight of the emulsion; (2) complete- or partial surface coating of surfaces, comprising applying the pickering emulsion completely or partially on the surface, covering the coated surface with a cover such the of water and solvent can escape, drying the covered, coated surface at least at a temperature of less than 40[deg] C, sintering the dried coating in the presence or absence of the cover; and (3) a conductive coating, which is transparent.

IPC 8 full level  
**C09D 5/24** (2006.01); **B22F 1/0545** (2022.01); **B22F 9/24** (2006.01); **C09D 7/61** (2018.01); **H01B 1/22** (2006.01); **H05K 1/09** (2006.01)

CPC (source: EP KR US)  
**B22F 1/0545** (2022.01 - EP KR US); **B22F 9/24** (2013.01 - KR); **B82Y 30/00** (2013.01 - EP US); **C09D 5/24** (2013.01 - EP KR US); **C09D 7/61** (2017.12 - EP US); **C09D 7/67** (2017.12 - EP US); **H01B 1/22** (2013.01 - EP KR US); **H05K 1/09** (2013.01 - KR); **H05K 1/097** (2013.01 - EP US); **B22F 2998/00** (2013.01 - EP US)

Citation (search report)  
See references of WO 2012084849A2

Cited by  
CN115401203A

Designated contracting state (EPC)  
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)  
**EP 2468826 A1 20120627**; BR 112013018452 A2 20180522; CA 2821844 A1 20120628; CN 103429673 A 20131204; EP 2655526 A2 20131030; JP 2014505969 A 20140306; KR 20140007359 A 20140117; SG 191736 A1 20130830; TW 201232566 A 20120801; US 2013337158 A1 20131219; WO 2012084849 A2 20120628; WO 2012084849 A3 20120816

DOCDB simple family (application)  
**EP 10196109 A 20101221**; BR 112013018452 A 20111219; CA 2821844 A 20111219; CN 201180065936 A 20111219; EP 11797328 A 20111219; EP 2011073276 W 20111219; JP 2013545277 A 20111219; KR 20137019291 A 20111219; SG 2013046735 A 20111219; TW 100147338 A 20111220; US 201113993516 A 20111219