

Title (en)  
NEODYMIUM/IRON/BORON-BASED PERMANENT MAGNET

Title (de)  
PERMANENTMAGNET AUF NEODYM/EISEN/BOR-BASIS

Title (fr)  
AIMANT PERMANENT À BASE DE NÉODYME/FER/BORE

Publication  
**EP 2721618 A1 20140423 (EN)**

Application  
**EP 12800074 A 20120615**

Priority  
• CN 201110172170 A 20110617  
• CN 2012077023 W 20120615

Abstract (en)  
[origin: WO2012171490A1] A sintered neodymium/iron/boron-based permanent magnet is provided. The permanent magnet comprises 16 to 25wt. % of Nd, 4 to 10 wt.% of Dy, 0 to 1.2 wt.% of Tb, 2 to 13 wt.% of component R, wherein component R is selected from Pr, Ce, Gd, or Y, or any combination thereof, 1.4 to 9 wt.% of component T, wherein component T is selected from Co, Cu, or Al, or any combination thereof, 0.1 to 0.6 wt. % of component M, wherein component M is selected from Zr, Ti, or Mo, or any combination thereof, 0.9 to 1.1 wt.% of B, and the balance of Fe. The permanent magnet only contains a limited amount of Dy and very little or even no Tb, and yet has high coercivity and high thermal stability. An electric motor, a generator and an integrated electromotor comprising the permanent magnet are also provided.

IPC 8 full level  
**H01F 1/057** (2006.01); **H01F 41/02** (2006.01)

CPC (source: EP)  
**C22C 33/0257** (2013.01); **C22C 38/002** (2013.01); **C22C 38/005** (2013.01); **C22C 38/06** (2013.01); **C22C 38/10** (2013.01); **C22C 38/14** (2013.01); **C22C 38/16** (2013.01); **H01F 1/0577** (2013.01); **H01F 41/0273** (2013.01); **B22F 2998/10** (2013.01); **C22C 2202/02** (2013.01)

Designated contracting state (EPC)  
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)  
**WO 2012171490 A1 20121220**; CN 102832003 A 20121219; EP 2721618 A1 20140423; EP 2721618 A4 20150708

DOCDB simple family (application)  
**CN 2012077023 W 20120615**; CN 201110172170 A 20110617; EP 12800074 A 20120615