

Title (en)

WIRE ROD HAVING SUPERIOR HYDROGEN DELAYED FRACTURE RESISTANCE, METHOD FOR MANUFACTURING SAME, HIGH STRENGTH BOLT USING SAME AND METHOD FOR MANUFACTURING BOLT

Title (de)

WALZDRAHT MIT HERVORRAGENDER WASSERSTOFFVERZÖGERTER BRUCHFESTIGKEIT, HERSTELLUNGSVERFAHREN DAFÜR, HOCHFESTER SCHRAUBBOLZEN DAMIT UND VERFAHREN ZUR HERSTELLUNG DES BOLZENS

Title (fr)

FIL MACHINE PRÉSENTANT UNE RÉSISTANCE SUPÉRIEURE À LA RUPTURE DIFFÉRÉE PAR HYDROGÈNE, SON PROCÉDÉ DE FABRICATION, BOULON À HAUTE RÉSISTANCE UTILISANT LEDIT FIL ET PROCÉDÉ DE FABRICATION DU BOULON

Publication

EP 2733229 A4 20150408 (EN)

Application

EP 12814354 A 20120514

Priority

- KR 20110070206 A 20110715
- KR 2012003757 W 20120514

Abstract (en)

[origin: EP2733229A1] The present invention relates to a wire rod used in bolts for automobile engines, for example, and more specifically to a wire rod having an improved resistance to hydrogen delayed fracture, to a manufacturing method for same, to a bolt using same and a method for manufacturing the bolt. Provided are a high strength wire rod having a superior resistance to hydrogen delayed fracture and a method for manufacturing same, a high strength bolt using the wire rod and a method for manufacturing same, wherein the wire rod comprises, 0.3-0.7 wt% C, 0.05-2.0 wt% Si, 0.7-1.5 wt% Mn, 0.01-0.1 wt% Ni, and 30-70 ppm La, and the remainder thereof is comprised by Fe and inevitable impurities.

IPC 8 full level

C21D 8/06 (2006.01); **C21D 9/00** (2006.01); **C21D 9/52** (2006.01); **C22C 38/00** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01);
C22C 38/08 (2006.01); **C22C 38/12** (2006.01)

CPC (source: EP KR US)

C21D 8/065 (2013.01 - EP KR US); **C21D 9/0093** (2013.01 - EP KR US); **C21D 9/525** (2013.01 - EP KR US); **C22C 38/005** (2013.01 - EP KR US);
C22C 38/02 (2013.01 - EP KR US); **C22C 38/04** (2013.01 - EP KR US); **C22C 38/08** (2013.01 - EP KR US); **C22C 38/12** (2013.01 - EP KR US)

Citation (search report)

- [XYI] JP S5884960 A 19830521 - KAWASAKI STEEL CO
- [YA] WO 2011016676 A2 20110210 - POSCO [KR], et al
- [IA] WO 0146485 A1 20010628 - NIPPON STEEL CORP [JP]
- [I] JP 2008274367 A 20081113 - SUMITOMO METAL IND
- [A] US 2007051432 A1 20070308 - KIMURA SEI [JP], et al
- [A] EP 1559805 A1 20050803 - KOBE STEEL LTD [JP]
- [A] US 2006289402 A1 20061228 - KIMURA SEI [JP], et al
- [A] JP 2001164337 A 20010619 - NIPPON STEEL CORP
- [A] JP H08170149 A 19960702 - KOBE STEEL LTD
- [A] JP 2008150683 A 20080703 - KOBE STEEL LTD
- [A] JP H06145889 A 19940527 - DAIDO STEEL CO LTD
- See references of WO 2013012161A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)

EP 2733229 A1 20140521; EP 2733229 A4 20150408; EP 2733229 B1 20160406; EP 2733229 B9 20160713; CN 103649354 A 20140319;
CN 103649354 B 20160706; JP 2014525987 A 20141002; JP 5826383 B2 20151202; KR 101325317 B1 20131108;
KR 20130009248 A 20130123; US 2014150934 A1 20140605; WO 2013012161 A1 20130124

DOCDB simple family (application)

EP 12814354 A 20120514; CN 201280035144 A 20120514; JP 2014520107 A 20120514; KR 20110070206 A 20110715;
KR 2012003757 W 20120514; US 201214232805 A 20120514