

Title (en)

METHOD AND DEVICE FOR TREATING A MOLTEN SLAG

Title (de)

VERFAHREN UND VORRICHTUNG ZUR BEHANDLUNG VON GESCHMOLZENER SCHLACKE

Title (fr)

PROCÉDÉ ET DISPOSITIF POUR TRAITER UN LAITIER FONDU

Publication

EP 2737091 A1 20140604 (EN)

Application

EP 12750856 A 20120726

Priority

- NL 2007190 A 20110728
- NL 2012050536 W 20120726

Abstract (en)

[origin: WO2013015690A1] A method for treating a calcium silicate-containing molten slag in a metallurgical process comprises: - producing a molten material from ore in a furnace, wherein a liquid molten slag is formed on the surface of the molten material; - separating the liquid molten slag from the molten material; - casting the separated liquid molten slag into a casting die; - cooling down of the molten slag in the casting die; wherein the method furthermore comprises: prior to casting, adding at least a first additive which comprises at least one alkali element-containing substance to the separated liquid molten slag in order to form a liquid slag alloy for reducing a solidification point of the liquid slag alloy with respect to a solidification point of the molten slag.

IPC 8 full level

C01B 25/02 (2006.01); **C04B 5/06** (2006.01); **C04B 18/14** (2006.01); **C21B 3/06** (2006.01); **C22B 7/04** (2006.01)

CPC (source: EP)

C04B 5/06 (2013.01); **C04B 18/142** (2013.01); **C04B 18/145** (2013.01); **C21B 3/06** (2013.01); **C22B 7/04** (2013.01); **C21B 2400/02** (2018.07);
C21B 2400/044 (2018.07); **Y02P 10/20** (2015.11); **Y02W 30/50** (2015.05); **Y02W 30/91** (2015.05)

Citation (search report)

See references of WO 2013015690A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)

WO 2013015690 A1 20130131; EP 2737091 A1 20140604; NL 2007190 C2 20130129

DOCDB simple family (application)

NL 2012050536 W 20120726; EP 12750856 A 20120726; NL 2007190 A 20110728