

Title (en)
WELDED STEEL PIPE WITH EXCELLENT WELDING HEAT-AFFECTED ZONE TOUGHNESS, AND PROCESS FOR PRODUCING SAME

Title (de)
GESCHWEISSTES STAHLROHR MIT HERVORRAGENDER SCHWEISSWÄRMEEINFLUSSZONENBESTÄNDIGKEIT UND VERFAHREN ZU SEINER HERSTELLUNG

Title (fr)
TUBE EN ACIER SOUDÉ POSSÉDANT UNE EXCELLENTE TÉNACITÉ DANS LA ZONE AFFECTÉE PAR LA CHALEUR DU SOUDAGE, ET PROCÉDÉ DE PRODUCTION DE CE TUBE

Publication
EP 2764946 A4 20150610 (EN)

Application
EP 12838033 A 20121003

Priority
• JP 2011219081 A 20111003
• JP 2012006332 W 20121003

Abstract (en)
[origin: EP2764946A1] It is an object to provide a welded steel pipe which is excellent in productivity and which has excellent welded heat-affected zone toughness without deteriorating the internal quality of welds. A welded steel pipe with excellent welded heat-affected zone toughness includes a butt weld formed by prior welding either an inner surface or an outer surface with a single layer for each of the inner and outer surfaces, wherein in the metallographic structure of a welded heat-affected zone, the martensite-austenite constituent (MA) area fraction is 4% or less, the average prior-austenite grain size is 400 μm or less, and the following items are taken into account: the average prior-austenite grain size of a welded heat-affected zone formed by prior welding, the average prior-austenite grain size of a welded heat-affected zone formed by subsequent welding, the bead width determined at a position 5 mm apart from the tip of a weld bead formed by subsequent welding, the fusion line tilt angle of a weld bead of prior welding, and the fusion line tilt angle of a weld bead of subsequent welding.

IPC 8 full level
B23K 9/025 (2006.01); **B21C 37/08** (2006.01); **B23K 9/18** (2006.01); **B23K 9/23** (2006.01); **B23K 33/00** (2006.01); **C22C 38/00** (2006.01); **C22C 38/58** (2006.01); **B23K 101/06** (2006.01); **B23K 103/04** (2006.01)

CPC (source: CN EP KR US)
B23K 9/0253 (2013.01 - EP KR US); **B23K 9/0282** (2013.01 - CN EP US); **B23K 9/18** (2013.01 - CN EP KR US); **B23K 33/006** (2013.01 - EP KR US); **C21D 8/105** (2013.01 - KR); **C21D 9/50** (2013.01 - CN EP US); **C22C 38/001** (2013.01 - CN EP US); **C22C 38/002** (2013.01 - CN EP US); **C22C 38/005** (2013.01 - EP US); **C22C 38/02** (2013.01 - CN EP US); **C22C 38/04** (2013.01 - CN EP US); **C22C 38/06** (2013.01 - CN EP US); **C22C 38/08** (2013.01 - CN EP US); **C22C 38/12** (2013.01 - CN EP US); **C22C 38/14** (2013.01 - CN EP US); **C22C 38/16** (2013.01 - CN EP US); **C22C 38/18** (2013.01 - CN EP US); **C22C 38/42** (2013.01 - CN EP US); **C22C 38/44** (2013.01 - CN EP US); **C22C 38/46** (2013.01 - CN EP KR US); **C22C 38/48** (2013.01 - CN EP KR US); **C22C 38/50** (2013.01 - CN EP US); **C22C 38/58** (2013.01 - CN EP US); **F16L 9/02** (2013.01 - US); **B23K 2101/10** (2018.07 - EP KR US); **B23K 2103/04** (2018.07 - EP KR US); **C21D 8/10** (2013.01 - CN EP US); **C21D 8/105** (2013.01 - CN EP US); **C21D 2211/001** (2013.01 - CN EP US); **C21D 2211/008** (2013.01 - CN EP KR US); **Y10T 428/12292** (2015.01 - EP US)

Citation (search report)
• [XY] EP 2036995 A1 20090318 - NIPPON STEEL CORP [JP]
• [ID] JP 2009202167 A 20090910 - JFE STEEL CORP
• [Y] JP H10298707 A 19981110 - SUMITOMO METAL IND
• [A] US 2010003535 A1 20100107 - HARA TAKUYA [JP], et al
• See references of WO 2013051249A1

Cited by
EP3392367A4; US11136653B2; EP3392366A4; EP3418411A4

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)
EP 2764946 A1 20140813; EP 2764946 A4 20150610; CN 103874558 A 20140618; JP 2013078775 A 20130502; KR 20140075734 A 20140619; RU 2014117665 A 20151110; US 2014227549 A1 20140814; WO 2013051249 A1 20130411

DOCDB simple family (application)
EP 12838033 A 20121003; CN 201280048892 A 20121003; JP 2011219081 A 20111003; JP 2012006332 W 20121003; KR 20147009915 A 20121003; RU 2014117665 A 20121003; US 201214348659 A 20121003