

Title (en)

Cold rolled steel flat product for deep drawing applications and method for its production

Title (de)

Kaltgewalztes Stahlflachprodukt für Tiefziehenwendungen und Verfahren zu seiner Herstellung

Title (fr)

Produit plat en acier laminé à froid pour applications d'emboutissage profond et son procédé de fabrication

Publication

EP 2767601 A1 20140820 (DE)

Application

EP 13155225 A 20130214

Priority

EP 13155225 A 20130214

Abstract (en)

The cold-rolled flat product made of steel, is claimed. The steel contains iron, unavoidable impurities, carbon, aluminum, niobium, titanium, phosphorus, sulfur, nitrogen, and optionally elements including manganese, rare earth metal, silicon, zirconium, vanadium, tungsten, molybdenum, chromium, cobalt, nickel, boron, copper and calcium. The product has deep drawability (r-value) of 1.3, and contains 0-0.1 vol.% of carbides. A ratio of a grain length in a rolling direction to a width in a transverse direction of a grain of the flat steel product is less than 1.5. The cold-rolled flat product made of steel, is claimed. The steel contains iron, unavoidable impurities, 0.05 wt.% of carbon, 6.8 wt.% of aluminum, 0.1-0.15 wt.% of niobium, 0.15-0.3 wt.% of titanium, less than 0.1 wt.% of phosphorus, less than 0.03 wt.% of sulfur, less than 0.1 wt.% of nitrogen, and optionally elements including 0-0.1 wt.% of manganese, 0-0.2 wt.% of rare earth metal, 0-2 wt.% of silicon, 0-1 wt.% of zirconium, 0-1 wt.% of vanadium, 0-1 wt.% of tungsten, 0-1 wt.% of molybdenum, 0-3 wt.% of chromium, 0-1 wt.% of cobalt, 0-2 wt.% of nickel, 0-0.1 wt.% of boron, 0-3 wt.% of copper and 0-0.015 wt.% of calcium. A ratio of titanium to niobium is 1.5-2.5. The product has deep drawability (r-value) of 1.3, and contains 0-0.1 vol.% of carbides. A ratio of a grain length in a rolling direction to a width in a transverse direction of a grain of the flat steel product is less than 1.5 An independent claim is included for a method of producing a cold-rolled flat product.

Abstract (de)

Die Erfindung betrifft ein kaltgewalztes Stahlflachprodukt für Tiefziehenwendungen aus einem Stahl, der neben Fe und unvermeidbaren Verunreinigungen (in Gew.-%) C: 0,008 - 0,1 %, Al: 6, 5 - 12 %, Nb: 0,1 - 0,2 %, Ti: 0, 15 - 0,5 %, P: < 0,1 %, S: < 0,03 %, N: < 0,1 % sowie optional eines oder mehrere Elemente aus der Gruppe "Mn, Si, REM, Mo, Cr, Zr, V, W, Co, Ni, B, Cu, Ca, N" mit der Maßgabe enthält, Mn: < 1 %, REM: < 0,2 %, Si: < 2 %, Zr: < 1 %, V: < 1 %, W: < 1 %, Mo: < 1 %, Cr: < 3 %, Co: < 1 %, Ni: < 2 %, B: < 0,1 %, Cu: < 3 %, Ca: < 0,015 %. Dabei gilt für das Verhältnis $2,5 \cdot \frac{\%Ti}{\%Nb} \cdot \frac{\%Ti}{\%Nb} \cdot \frac{\%Ti}{\%Nb} = 1,5$, $\%Ti = Ti\text{-Gehalt}$ und $\%Nb = Nb\text{-Gehalt}$. Zur Herstellung eines solchen Stahlflachprodukts wird ein entsprechend zusammengesetzter Stahl zu einem Vorprodukt vergossen, das dann bei einer Warmwalzendtemperatur von 820 - 1000 °C zu Warmband warmgewalzt wird. Dieses wird anschließend bei einer Haspeltemperatur von bis zu 750 °C gehaspelt, nach dem Haspeln bei einer Glühtemperatur von >650 - 1200 °C über 1 - 50 h geglüht, anschließend in ein oder mehr Stufen mit einem Gesamt-Kaltwalzgrad von $\approx 65\%$ zum kaltgewalzten Stahlflachprodukt kaltgewalzt und schließlich bei 650 - 850 °C schlussgeglüht.

IPC 8 full level

C21D 8/04 (2006.01); **C21D 9/48** (2006.01); **C22C 38/06** (2006.01); **C22C 38/12** (2006.01); **C22C 38/14** (2006.01)

CPC (source: EP US)

C21D 1/26 (2013.01 - EP US); **C21D 6/004** (2013.01 - EP US); **C21D 6/005** (2013.01 - EP US); **C21D 6/008** (2013.01 - EP US); **C21D 8/0263** (2013.01 - EP US); **C21D 8/0405** (2013.01 - EP US); **C21D 9/46** (2013.01 - EP US); **C21D 9/48** (2013.01 - EP US); **C22C 38/001** (2013.01 - US); **C22C 38/004** (2013.01 - US); **C22C 38/02** (2013.01 - US); **C22C 38/04** (2013.01 - US); **C22C 38/06** (2013.01 - EP US); **C22C 38/12** (2013.01 - EP US); **C22C 38/14** (2013.01 - EP US); **C22C 38/44** (2013.01 - US); **C22C 38/46** (2013.01 - US); **C22C 38/48** (2013.01 - US); **C22C 38/50** (2013.01 - US); **C21D 8/0226** (2013.01 - EP US); **C21D 8/0236** (2013.01 - EP US); **C21D 2211/004** (2013.01 - EP US); **C21D 2211/005** (2013.01 - EP US)

Citation (applicant)

S. U. BRÜX: "Tiefziehfähige Eisen-Aluminium-Leichtbaustähle", KONSTRUKTION, 4 April 2002 (2002-04-04)

Citation (search report)

- [I] EP 0826787 A2 19980304 - KRUPP AG HOESCH KRUPP [DE], et al
- [A] JP 2007321168 A 20071213 - JFE STEEL KK
- [A] JP 2001271136 A 20011002 - NISSHIN STEEL CO LTD
- [A] US 2010300585 A1 20101202 - PERLADE ASTRID [FR], et al
- [A] GB 1044801 A 19661005 - YAWATA IRON & STEEL CO
- [A] JP 2010121213 A 20100603 - NIPPON STEEL CORP, et al
- [A] BRUX U ET AL: "Light-weight steels based on iron-aluminium - Influence of micro alloying elements (B, Ti, Nb) on microstructures, textures and mechanical properties", STEEL RESEARCH, DUESSELDORF, DE, vol. 73, no. 12, 1 December 2002 (2002-12-01), pages 543 - 548, XP009170715, ISSN: 0177-4832

Cited by

EP3225702A1; WO2017050558A1; WO2017167778A1; US2017002436A1; US11970757B2; WO2017021464A1; DE102015116186A1; WO2020078529A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

EP 2767601 A1 20140820; **EP 2767601 B1 20181010**; BR 112015019413 A2 20170718; CN 105121673 A 20151202; CN 110295317 A 20191001; JP 2016511795 A 20160421; JP 6383368 B2 20180829; KR 102193066 B1 20201221; KR 20150119230 A 20151023; US 10513762 B2 20191224; US 2016017467 A1 20160121; WO 2014125016 A1 20140821

DOCDB simple family (application)

EP 13155225 A 20130214; BR 112015019413 A 20140213; CN 201480021223 A 20140213; CN 201910355506 A 20140213;
EP 2014052810 W 20140213; JP 2015557422 A 20140213; KR 20157024979 A 20140213; US 201414767741 A 20140213