

Title (en)

PROCESS ENGINEERING MEASURES IN A STRAND CASTING MACHINE AT THE BEGINNING OF CASTING, AT THE END OF CASTING, AND DURING THE MANUFACTURING OF A TRANSITION PIECE

Title (de)

PROZESSTECHNISCHE MASSNAHMEN IN EINER STRANGGIESSMASCHINE BEI GIESSSTART, BEI GIESSENDE UND BEI DER HERSTELLUNG EINES ÜBERGANGSSTÜCKS

Title (fr)

MESURES D'AMÉLIORATION DU PROCESSUS DANS UNE MACHINE DE COULÉE CONTINUE AU DÉMARRAGE DE LA COULÉE, À LA FIN DE LA COULÉE ET LORS DE LA PRODUCTION D'UN ÉLÉMENT DE JONCTION

Publication

**EP 2788133 A1 20141015 (DE)**

Application

**EP 12798200 A 20121119**

Priority

- AT 17922011 A 20111205
- EP 2012072959 W 20121119

Abstract (en)

[origin: WO2013083391A1] The present invention relates to in each case one method for the operation of a strand casting machine (1) at the beginning of casting, at the end of casting, and during the manufacturing of a transition piece (21). The problem addressed by the invention is that of - improving the quality of the strand ends (16, 18) and - preventatively protecting the strand casting machine (1) against damage during the implementation of the method. Said problem is solved by means of a method for the operation of a strand casting machine (1) at the beginning of casting by means of the following additional method steps: - detecting a position of the beginning of the strand (16) in the strand guide (4); - after the beginning of the strand (16), preferably an upper end (17a) of the beginning region of the strand (17) has passed the pair of adjustable strand-guiding rollers (5); adjusting the pair against the strand (2) such that the pair makes contact with the strand (2); - cooling the beginning region of the strand (17) with  $Q < Q_{\text{Nenn}}$ , wherein the cooling nozzle (10) discharges a coolant flow rate  $Q$  lower than a nominal coolant flow rate  $Q_{\text{Nenn}}$  onto the beginning region of the strand (17); and - cooling the main part of the strand (20) with  $Q \approx Q_{\text{Nenn}}$ , wherein the cooling nozzle (10) discharges a coolant flow rate  $Q$  substantially equal to  $Q_{\text{Nenn}}$  onto the main part of the strand (20).

IPC 8 full level

**B22D 11/08** (2006.01); **B22D 11/04** (2006.01); **B22D 11/16** (2006.01); **B22D 11/20** (2006.01); **B22D 11/22** (2006.01)

CPC (source: AT EP RU US)

**B22D 11/04** (2013.01 - EP US); **B22D 11/081** (2013.01 - US); **B22D 11/083** (2013.01 - AT); **B22D 11/12** (2013.01 - AT);  
**B22D 11/124** (2013.01 - AT); **B22D 11/128** (2013.01 - AT); **B22D 11/14** (2013.01 - AT); **B22D 11/161** (2013.01 - AT EP US);  
**B22D 11/208** (2013.01 - EP US); **B22D 11/225** (2013.01 - AT EP US); **B22D 11/16** (2013.01 - RU)

Citation (search report)

See references of WO 2013083391A1

Cited by

EP3437757A1; EP3437756A1; EP3437759A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)

**WO 2013083391 A1 20130613**; AT 512214 A1 20130615; AT 512214 B1 20150415; CN 103958094 A 20140730; CN 103958094 B 20160217;  
EP 2788133 A1 20141015; EP 2788133 B1 20160203; KR 101984634 B1 20190531; KR 20140101414 A 20140819;  
RU 2012152085 A 20140610; RU 2620320 C2 20170524; US 2014290899 A1 20141002; US 9254520 B2 20160209

DOCDB simple family (application)

**EP 2012072959 W 20121119**; AT 17922011 A 20111205; CN 201280059916 A 20121119; EP 12798200 A 20121119;  
KR 20147018831 A 20121119; RU 2012152085 A 20121204; US 201214361284 A 20121119