

Title (en)
SINTERED TUNGSTEN ALLOY

Title (de)
GESINTERTE WOLFRAMLEGIERUNG

Title (fr)
ALLIAGE DE TUNGSTÈNE FRITTÉ

Publication
EP 2789708 A1 20141015 (EN)

Application
EP 12856450 A 20121127

Priority
• JP 2011267845 A 20111207
• JP 2012080565 W 20121127

Abstract (en)
There is provided a flat plate-like sintered tungsten alloy that can be molded into a complex shape by press working or forge processing. The flat plate-like sintered tungsten alloy contains 85% by mass or more and 98% by mass or less of W, 1.4% by mass or more and 11% by mass or less of Ni, and 0.6% by mass or more and 6% by mass or less of at least one substance selected from the group consisting of Fe, Cu and Co, wherein an elongation percentage of the flat plate-like sintered tungsten alloy in a planar direction is 20% or more.

IPC 8 full level
C22C 27/04 (2006.01); **B22F 3/24** (2006.01); **C22C 1/04** (2006.01); **C22F 1/00** (2006.01); **C22F 1/18** (2006.01)

CPC (source: EP US)
B22F 3/24 (2013.01 - EP US); **B22F 5/006** (2013.01 - EP US); **C22C 1/045** (2013.01 - EP US); **C22C 27/04** (2013.01 - EP US); **C22F 1/02** (2013.01 - EP US); **C22F 1/18** (2013.01 - EP US); **Y10T 428/12014** (2015.01 - EP US)

Cited by
EP3229268A4; CN106756379A; RU2623566C1

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)
EP 2789708 A1 20141015; **EP 2789708 A4 20151014**; JP 5805213 B2 20151104; JP 5847196 B2 20160120; JP WO2013084748 A1 20150427; JP WO2013084749 A1 20150427; US 2014308536 A1 20141016; WO 2013084748 A1 20130613; WO 2013084749 A1 20130613

DOCDB simple family (application)
EP 12856450 A 20121127; JP 2012080564 W 20121127; JP 2012080565 W 20121127; JP 2013548184 A 20121127; JP 2013548185 A 20121127; US 201214363401 A 20121127