

Title (en)
BISMUTH CONTAINING FREE-MACHINING STEEL

Title (de)
BISMUTHALTIGER AUTOMATENSTAHL

Title (fr)
ACIER DE DÉCOLLETAGE CONTENANT DU BISMUTH

Publication
EP 2789710 B1 20190821 (DE)

Application
EP 13827542 A 20130212

Priority
• RU 2012133578 A 20120806
• RU 2013000105 W 20130212

Abstract (en)
[origin: RU2503737C1] FIELD: metallurgy.SUBSTANCE: proposed steel contains components in the following ratio in wt %: carbon - not over 0.16; silicon - not over 0.15; manganese - 1.2-1.68; sulfur - 0.2-0.4; phosphorus - 0.06-0.15; aluminium - not over 0.01; bismuth - 0.03-0.05 or 0.06-0.12, oxygen - 0.003-0.015, iron and admixtures making the rest. It features uniformly distributed sulphide inclusions approximating to globular and slightly deformed form and oxygen activity at transfer to casting of 20-70 ppm.EFFECT: calibrated products feature higher machinability by cutting at required level of mechanical properties.6 dwg, 2 tbl

IPC 8 full level
C22C 38/60 (2006.01); **C22C 38/00** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01)

CPC (source: EP)
C22C 38/00 (2013.01); **C22C 38/02** (2013.01); **C22C 38/04** (2013.01); **C22C 38/60** (2013.01); **C21D 2211/004** (2013.01)

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)
EP 2789710 A1 20141015; EP 2789710 A4 20150520; EP 2789710 B1 20190821; CN 104245992 A 20141224; CN 104245992 B 20161214;
ES 2757277 T3 20200428; RU 2503737 C1 20140110; WO 2014025287 A1 20140213

DOCDB simple family (application)
EP 13827542 A 20130212; CN 201380010511 A 20130212; ES 13827542 T 20130212; RU 2012133578 A 20120806;
RU 2013000105 W 20130212