

Title (en)
MICROPOROUS POLYVINYLDENE FLUORIDE MEMBRANE

Title (de)
MIKROPORÖSE POLYVINYLDENFLUORID-MEMBRAN

Title (fr)
MEMBRANE DE FLUORURE DE POLYVINYLIDÈNE MICROPOREUSE

Publication
EP 3003538 A1 20160413 (DE)

Application
EP 14727763 A 20140522

Priority

- EP 13169698 A 20130529
- EP 2014060527 W 20140522
- EP 14727763 A 20140522

Abstract (en)

[origin: WO2014191296A1] The invention relates to a hydrophobic hollow fiber membrane made of a vinylidene fluoride polymer, with a wall, a wall thickness, an outer surface on the membrane outer face, an inner surface on the membrane inner face facing the membrane lumen, and a support layer adjoining the inner surface with a substantially isotropic pore structure over the wall thickness, said pore structure extending over at least 80% of the wall thickness and having pores with an average diameter of less than 1 μm , wherein the hollow fiber membrane has pores in the membrane outer surface and in the membrane inner surface. The invention is characterized in that the vinylidene fluoride polymer has an average molecular weight MW ranging from 555,000 to 700,000 Dalton and a polydispersity greater than 3.0; the pores in the outer and the inner surface are formed in the shape of islands and the ratio of the longitudinal extension to the transverse extension of the pores is no greater than 10; the porosity ranges from 0 to 90 vol.%; the wall thickness ranges from 50 to 300 μm ; the diameter of the lumen ranges from 100 to 500 μm ; and the hollow fiber membrane has a maximum separation pore diameter d_{max} , ascertained according to the bubble point method, ranging from 0.3 to 0.7 μm .

IPC 8 full level
B01D 67/00 (2006.01); **B01D 61/36** (2006.01); **B01D 69/02** (2006.01); **B01D 69/08** (2006.01); **B01D 71/32** (2006.01); **B01D 71/34** (2006.01); **B01D 71/76** (2006.01)

CPC (source: EP US)
B01D 61/364 (2013.01 - EP US); **B01D 67/0018** (2013.01 - EP US); **B01D 69/02** (2013.01 - EP US); **B01D 69/081** (2013.01 - US); **B01D 69/087** (2013.01 - EP US); **B01D 71/34** (2013.01 - EP US); **B01D 71/76** (2013.01 - EP US); **B01D 71/32** (2013.01 - EP US); **B01D 2325/026** (2013.01 - US); **B01D 2325/04** (2013.01 - US); **B01D 2325/24** (2013.01 - EP US); **B01D 2325/38** (2013.01 - US)

Citation (examination)

- "Solef® & Hylar® PVDF Polyvinylidene fluoride Design and Processing Guide", 27 July 2009 (2009-07-27), pages 1 - 72, XP055453863, Retrieved from the Internet <URL:https://www.equiflow.com/sites/default/files/bijlagen/bestanden/solef_hylar_2009.pdf> [retrieved on 20180223]
- SOLVAY: "SPECIALTY POLYMERS Solef PVDF Design & Processing Guide", 20 December 2017 (2017-12-20), XP055584423, Retrieved from the Internet <URL:https://www.solvay.com/sites/g/files/srpend221/files/2018-08/Solef-PVDF-Design-and-Processing-Guide_EN-v2.7_0.pdf> [retrieved on 20190430]
- "Solution Processing Guide for Polymer Membranes Introduction", TECHNICAL BULLETIN, SOLVAY ADVANCED POLYMERS, 1 January 2008 (2008-01-01), pages 10 pp, XP055184321, Retrieved from the Internet <URL:http://doc.diytrade.com/docdvr/450410/43218107/1427599665.pdf> [retrieved on 20150420]
- See also references of WO 2014191296A1

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)
BA ME

DOCDB simple family (publication)
WO 2014191296 A1 20141204; CN 105473214 A 20160406; CN 105473214 B 20180615; EP 3003538 A1 20160413; EP 3003538 B1 20210505; JP 2016523698 A 20160812; JP 6438012 B2 20181212; KR 102205185 B1 20210120; KR 20160012230 A 20160202; US 10946345 B2 20210316; US 2016089638 A1 20160331

DOCDB simple family (application)
EP 2014060527 W 20140522; CN 201480042387 A 20140522; EP 14727763 A 20140522; JP 2016515734 A 20140522; KR 20157037050 A 20140522; US 201414893274 A 20140522