

Title (en)

COPPER ALLOY, COPPER ALLOY THIN SHEET AND COPPER ALLOY MANUFACTURING METHOD

Title (de)

KUPFERLEGIERUNG, FEINBLECH AUS KUPFERLEGIERUNG UND VERFAHREN ZUR HERSTELLUNG EINER KUPFERLEGIERUNG

Title (fr)

ALLIAGE DE CUIVRE, FEUILLE MINCE EN ALLIAGE DE CUIVRE ET PROCÉDÉ DE FABRICATION D'ALLIAGE DE CUIVRE

Publication

**EP 3031937 A1 20160615 (EN)**

Application

**EP 14834900 A 20140808**

Priority

- JP 2013167045 A 20130809
- JP 2014116287 A 20140604
- JP 2014070981 W 20140808

Abstract (en)

Provided is a copper alloy containing 1.5 to 2.7% by mass of Fe, 0.008 to 0.15% by mass of P, and 0.01 to 0.5% by mass of Zn, the balance being Cu and inevitable impurities. The amount of C contained as one of the inevitable impurities is less than 3 ppm by mass.

IPC 8 full level

**C22C 9/00** (2006.01); **B22D 21/00** (2006.01); **C22F 1/00** (2006.01)

CPC (source: EP)

**B22D 11/004** (2013.01); **B22D 21/025** (2013.01); **C22C 9/00** (2013.01); **C22F 1/08** (2013.01)

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

**EP 3031937 A1 20160615**; **EP 3031937 A4 20170705**; CN 105452500 A 20160330; CN 105452500 B 20170815; JP 2015057511 A 20150326; JP 5866410 B2 20160217; KR 102213955 B1 20210209; KR 20160041914 A 20160418; TW 201522670 A 20150616; TW I522483 B 20160221; WO 2015020187 A1 20150212

DOCDB simple family (application)

**EP 14834900 A 20140808**; CN 201480044186 A 20140808; JP 2014070981 W 20140808; JP 2014116287 A 20140604; KR 20167003211 A 20140808; TW 103127249 A 20140808