

Title (en)

LOW DENSITY RHENIUM-FREE NICKEL BASE SUPERALLOY

Title (de)

RHENIUMFREIE NICKELBASIS-SUPERLEGIERUNG MIT NIEDRIGER DICHT

Title (fr)

SUPERALLIAGE À BASE DE NICKEL SANS RHÉNIUM À FAIBLE DENSITÉ

Publication

EP 3091095 B1 20180711 (DE)

Application

EP 15166317 A 20150505

Priority

EP 15166317 A 20150505

Abstract (en)

[origin: US2017058383A1] The invention relates to a substantially rhenium-free nickel base alloy showing a high creep resistance and relatively low density which comprises in % by weight: aluminum from 3.0 to 7.7, cobalt from 0 to 16.8, chromium from 3 to 11.8, molybendum from 3.1 to 11.3, tantalum from 0 to 3.9. In addition to nickel and unavoidable impurities this alloy may further comprise one or more of titanium, tungsten, carbon, phosphorus, copper, zirconium, silicon, hafnium, yttrium, niobium, and germanium.

IPC 8 full level

C22C 19/05 (2006.01)

CPC (source: EP US)

C22C 1/023 (2013.01 - EP US); **C22C 19/05** (2013.01 - EP US); **C22C 19/057** (2013.01 - EP US); **C22F 1/10** (2013.01 - EP US)

Cited by

CN112760525A

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)

EP 3091095 A1 20161109; EP 3091095 B1 20180711; ES 2682362 T3 20180920; US 2017058383 A1 20170302

DOCDB simple family (application)

EP 15166317 A 20150505; ES 15166317 T 20150505; US 201615142068 A 20160429