

Title (en)  
HARDENED NICKEL-CHROMIUM-TITANIUM-ALUMINUM ALLOY WITH GOOD WEAR RESISTANCE, CREEP RESISTANCE, CORROSION RESISTANCE AND WORKABILITY

Title (de)  
AUSHÄRTENDE NICKEL-CHROM-TITAN-ALUMINIUM-LEGIERUNG MIT GUTER VERSCHLEISSBESTÄNDIGKEIT, KRIECHFESTIGKEIT, KORROSIONSBESTÄNDIGKEIT UND VERARBEITBARKEIT

Title (fr)  
ALLIAGE NICKEL-CHROME-TITANE-ALUMINIUM DURCISSANT PAR TREMPE ET PRÉSENTANT UNE BONNE RÉSISTANCE À L'USURE, AU FLUAGE ET À LA CORROSION, ET UNE BONNE USINABILITÉ

Publication  
**EP 3102712 B1 20180613 (DE)**

Application  
**EP 15704949 A 20150112**

Priority  
• DE 102014001329 A 20140204  
• DE 2015000009 W 20150112

Abstract (en)  
[origin: WO2015117585A2] The invention relates to hardened nickel-chromium-titanium-aluminum wrought alloy with good wear resistance as well as very good resistance to corrosion at a high temperature, good creep resistance, and good workability containing, (in mass %) 5 - 35% chromium, 1.0 - 3.0% titanium, 0.6 - 2.0% aluminum, 0.005 - 0.10% carbon, 0.0005 - 0.050% nitrogen, 0.0005 - 0.030% phosphorus, max. 0.010% sulfur, max. 0.020% oxygen, max. 0.70% silicon, max. 2.0% manganese, max. 0.05% magnesium, max. 0.05% calcium, max. 2.0% molybdenum, max. 2.0% tungsten, max. 0.5 % niobium, max. 0.5% copper, max. 0.5 % vanadium, if required, 0 - 20% Fe, if required, 0 - 15% cobalt, if required 0 - 0.20% Zr, if required 0.0001 - 0.008% boron, the remainder being nickel and the usual impurities related to the method. The nickel content is greater than 35%. The relation of  $Cr + Fe + Co \geq 26\%$  (1) must be fulfilled in order to achieve good wear resistance and the relation  $fh \geq 0$  (2a) in which  $fh = 6.49 + 3.88 Ti + 1.36 Al - 0.301 Fe + (0.759 - 0.0209 Co) Co - 0.428 Cr - 28.2 C$  (2) must be fulfilled so that a sufficient solidness at high temperatures is obtained, Ti, Al, Fe, Co, Cr and C corresponding to the concentration of the relevant elements in mass % and fh in %.

IPC 8 full level  
**C22C 19/05** (2006.01)

CPC (source: CN EP KR US)  
**C22C 19/053** (2013.01 - CN EP KR US); **C22C 19/055** (2013.01 - KR); **C22C 19/058** (2013.01 - CN EP KR US); **F01L 3/02** (2013.01 - US)

Designated contracting state (EPC)  
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)  
**DE 102014001329 A1 20150806; DE 102014001329 B4 20160428**; BR 112016012102 A2 20170926; BR 112016012102 B1 20210105; CN 106103759 A 20161109; CN 106103759 B 20180904; EP 3102712 A2 20161214; EP 3102712 B1 20180613; JP 2017508885 A 20170330; JP 6370392 B2 20180808; KR 101824865 B1 20180202; KR 20160130991 A 20161115; SI 3102712 T1 20181030; US 11098389 B2 20210824; US 2016312341 A1 20161027; WO 2015117585 A2 20150813; WO 2015117585 A3 20151022

DOCDB simple family (application)  
**DE 102014001329 A 20140204**; BR 112016012102 A 20150112; CN 201580003100 A 20150112; DE 2015000009 W 20150112; EP 15704949 A 20150112; JP 2016550785 A 20150112; KR 20167021394 A 20150112; SI 201530371 T 20150112; US 201515104306 A 20150112