

Title (en)  
ACRYLIC RESIN COMPOSITION, ACRYLIC RESIN FILM, AND MOLDED BODY

Title (de)  
ACRYLHARZZUSAMMENSETZUNG, ACRYLHARZFOLIE UND FORMKÖRPER

Title (fr)  
COMPOSITION DE RÉSINE ACRYLIQUE, FILM DE RÉSINE ACRYLIQUE ET CORPS MOULÉ

Publication  
**EP 3130637 A1 20170215 (EN)**

Application  
**EP 15776958 A 20150408**

Priority  
• JP 2014079340 A 20140408  
• JP 2014179805 A 20140904  
• JP 2015060994 W 20150408

Abstract (en)  
The present invention addresses the issue of providing an acrylic resin composition having high weather resistance, flexibility, heat resistance, transparency, and stress-whitening resistance. This issue is solved by an acrylic resin composition containing a rubber-containing multi-stage polymer (I) containing at least 30% by mass of an elastic polymer (A). (1) The total light transmittance is at least 90% for a molded body having a thickness of 1 mm and produced by heating and melting powdered acrylic resin composition, then pressurizing the composition at a temperature of 200 °C and a pressure of 5 MPa for 5 minutes, then cooling same for 5 minutes while applying a pressure of 2 MPa; and (2) having a difference (#W) in whiteness before and after elongation of no more than 1, when a test piece (1) comprising said molded body and having a length of 80 mm and width of 15 mm or a test piece (2), that is obtained by membrane formation from the acrylic resin composition by using the T-die method and has a thickness of 0.05-0.1 mm, a length of 80 mm, and a width of 15 mm, is stretched in accordance with ISO527 by 10 mm at a tension speed of 500 mm/min at a temperature of 23 °C, having an initial chuck-to-chuck distance of 25 mm and a final chuck-to-chuck distance of 35 mm.

IPC 8 full level  
**B32B 27/30** (2006.01); **C08F 265/06** (2006.01); **C08J 7/043** (2020.01); **C08J 7/046** (2020.01); **C08L 51/06** (2006.01)

CPC (source: EP IL KR US)  
**B29C 43/24** (2013.01 - IL US); **B29C 43/305** (2013.01 - IL US); **B29C 55/02** (2013.01 - IL US); **B32B 15/082** (2013.01 - IL KR US); **B32B 27/30** (2013.01 - IL KR); **B32B 27/308** (2013.01 - IL US); **C08F 265/06** (2013.01 - EP IL KR US); **C08F 265/08** (2013.01 - IL KR); **C08F 285/00** (2013.01 - EP IL KR); **C08J 5/18** (2013.01 - EP IL KR US); **C08J 7/0427** (2020.01 - EP IL US); **C08J 7/043** (2020.01 - EP US); **C08J 7/046** (2020.01 - EP US); **C08L 51/003** (2013.01 - EP IL US); **C08L 51/06** (2013.01 - IL KR US); **B29K 2033/08** (2013.01 - IL US); **B29K 2995/0016** (2013.01 - IL US); **B29K 2995/0026** (2013.01 - IL US); **B29K 2995/0046** (2013.01 - IL US); **B29K 2995/0082** (2013.01 - IL US); **B29K 2995/0087** (2013.01 - IL US); **B29L 2009/00** (2013.01 - IL US); **B32B 2307/306** (2013.01 - IL US); **B32B 2307/412** (2013.01 - IL US); **B32B 2307/712** (2013.01 - IL US); **C08F 285/00** (2013.01 - US); **C08F 2500/12** (2013.01 - IL US); **C08F 2800/20** (2013.01 - IL US); **C08J 2351/06** (2013.01 - IL US); **C08J 2433/12** (2013.01 - EP IL US); **C08J 2451/00** (2013.01 - EP IL US); **C08J 2451/04** (2013.01 - EP IL US); **C08L 2201/10** (2013.01 - EP IL US); **C08L 2203/16** (2013.01 - EP IL US); **C08L 2205/025** (2013.01 - EP IL US); **C08L 2207/53** (2013.01 - EP IL US)

Cited by  
US10920067B2

Designated contracting state (EPC)  
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)  
BA ME

DOCDB simple family (publication)  
**EP 3130637 A1 20170215**; **EP 3130637 A4 20170614**; **EP 3130637 B1 20220810**; CN 106170514 A 20161130; CN 106170514 B 20211126; IL 248194 A0 20161130; IL 248194 B 20200831; JP 6716916 B2 20200701; JP WO2015156323 A1 20170413; KR 20160130812 A 20161114; KR 20180051665 A 20180516; US 2017114215 A1 20170427; WO 2015156323 A1 20151015

DOCDB simple family (application)  
**EP 15776958 A 20150408**; CN 201580018814 A 20150408; IL 24819416 A 20161005; JP 2015060994 W 20150408; JP 2015521158 A 20150408; KR 20167027472 A 20150408; KR 20187012670 A 20150408; US 201515302603 A 20150408