

Title (en)  
COLD-ROLLED STEEL SHEET HAVING EXCELLENT SPOT WELDABILITY, AND MANUFACTURING METHOD THEREFOR

Title (de)  
KALTGEWALZTES STAHLBLECH MIT EXZELLENTER PUNKTSCHWEISSBARKEIT UND HERSTELLUNGSVERFAHREN DAFÜR

Title (fr)  
TÔLE EN ACIER LAMINÉE À FROID DOTÉE D'EXCELLENTE PROPRIÉTÉS DE SOUDAGE PAR POINT, ET PROCÉDÉ DE FABRICATION DE CELLE-CI

Publication  
**EP 3178954 A4 20180110 (EN)**

Application  
**EP 15829208 A 20150731**

Priority  
• JP 2014162834 A 20140808  
• JP 2015003881 W 20150731

Abstract (en)  
[origin: EP3178954A1] A cold-rolled steel sheet having excellent spot weldability suitable for use in vehicles, electric appliances, etc. is provided. The cold-rolled steel sheet has a steel composition containing, in mass%: C: 0.05% to 0.13%; Si: 0.05% to 2.0%; Mn: 1.5% to 4.0%; P: 0.05% or less; S: 0.005% or less; Al: 0.01% to 0.10%; Cr: 0.05% to 1.0%; Nb: 0.010% to 0.070%; Ti: 0.005% to 0.040%; and N: 0.0005% to 0.0065%, with a mass ratio Ti/N of Ti and N being 2.5 or more and 7.5 or less, and a balance being Fe and incidental impurities, wherein 70 mass% or more of Ti in steel exists as a precipitate, and 15 mass% or more of Nb in the steel exists as solute Nb, and a tensile strength is 980 MPa or more.

IPC 8 full level  
**C22C 38/00** (2006.01); **C21D 1/26** (2006.01); **C21D 8/02** (2006.01); **C21D 9/46** (2006.01); **C22C 38/02** (2006.01); **C22C 38/06** (2006.01); **C22C 38/20** (2006.01); **C22C 38/22** (2006.01); **C22C 38/24** (2006.01); **C22C 38/26** (2006.01); **C22C 38/28** (2006.01); **C22C 38/38** (2006.01); **C22C 38/42** (2006.01); **C22C 38/48** (2006.01); **C22C 38/50** (2006.01); **C22C 38/58** (2006.01)

CPC (source: EP US)  
**C21D 1/26** (2013.01 - EP US); **C21D 8/0205** (2013.01 - EP US); **C21D 8/0226** (2013.01 - EP US); **C21D 8/0236** (2013.01 - EP US); **C21D 8/0263** (2013.01 - EP US); **C21D 9/46** (2013.01 - EP US); **C22C 38/00** (2013.01 - EP US); **C22C 38/001** (2013.01 - EP US); **C22C 38/002** (2013.01 - EP US); **C22C 38/02** (2013.01 - EP US); **C22C 38/06** (2013.01 - EP US); **C22C 38/20** (2013.01 - EP US); **C22C 38/22** (2013.01 - EP US); **C22C 38/24** (2013.01 - EP US); **C22C 38/26** (2013.01 - EP US); **C22C 38/28** (2013.01 - EP US); **C22C 38/38** (2013.01 - EP US); **C22C 38/42** (2013.01 - EP US); **C22C 38/48** (2013.01 - EP US); **C22C 38/50** (2013.01 - EP US); **C22C 38/58** (2013.01 - EP US)

Citation (search report)  
• [X] EP 2578718 A1 20130410 - JFE STEEL CORP [JP]  
• [X] EP 2426230 A1 20120307 - JFE STEEL CORP [JP]  
• [A] US 2004238082 A1 20041202 - HASEGAWA KOHEI [JP], et al  
• [A] WO 2013073136 A1 20130523 - JFE STEEL CORP [JP]  
• [A] US 2013153096 A1 20130620 - HAMADA KAZUYUKI [JP], et al  
• [A] US 6264760 B1 20010724 - TAMEHIRO HIROSHI [JP], et al  
• See references of WO 2016021169A1

Designated contracting state (EPC)  
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)  
**EP 3178954 A1 20170614; EP 3178954 A4 20180110; EP 3178954 B1 20190306**; CN 106661693 A 20170510; CN 106661693 B 20180911; JP 2016037650 A 20160322; JP 5935843 B2 20160615; MX 2017001687 A 20170427; US 2017204492 A1 20170720; WO 2016021169 A1 20160211

DOCDB simple family (application)  
**EP 15829208 A 20150731**; CN 201580042291 A 20150731; JP 2014162834 A 20140808; JP 2015003881 W 20150731; MX 2017001687 A 20150731; US 201515329026 A 20150731