

Title (en)

DEVICE FOR IMPROVING THE ACOUSTIC PROPERTIES OF SPRUCE TONE WOOD

Title (de)

VERFAHREN ZUR VERBESSERUNG DER AKUSTISCHEN EIGENSCHAFTEN VON FICHTEN-KLANGHOLZ

Title (fr)

PROCÉDÉ DESTINÉ A L'AMÉLIORATION DES PROPRIÉTÉS ACOUSTIQUES DU BOIS DE RÉSONANCE D'ÉPICEA

Publication

EP 3232432 A1 20171018 (DE)

Application

EP 16164755 A 20160411

Priority

EP 16164755 A 20160411

Abstract (de)

Bei einem Verfahren zur Verbesserung der akustischen Eigenschaften von Fichten-Klangholz für Musikinstrumente wird mindestens ein Klangholzrohling unter kontrollierten, sterilen Bedingungen einer Behandlung mit *Physisporinus vitreus* unterzogen. Dabei wird der vorgängig sterilisierte Klangholzrohling in ein mit Pilzmyzel angereichertes Flüssigmedium getaucht und darin während einer Einwirkungszeit im Dunkeln gehalten und abschliessend sterilisiert, wobei während der Einwirkungszeit eine Temperatur von 18 bis 26°C und eine relative Luftfeuchte von ungefähr 60 bis ungefähr 80% eingestellt wird. Dadurch, dass das Flüssigmedium nanofibrillierte Cellulose (NFC) in einem Anteil von 200 bis 300 g pro Liter enthält, wird eine reproduzierbare, gleichmässige und von lokalen Fehlstellen freie Verbesserung der akustischen Eigenschaften des Klangholzes gewährleistet.

IPC 8 full level

G10D 1/00 (2006.01)

CPC (source: EP)

G10C 3/06 (2013.01); **G10D 3/22** (2020.02); **H04R 1/02** (2013.01); **H04R 2201/029** (2013.01)

Citation (applicant)

- EP 1734504 A1 20061220 - SCHLESKE MARTIN [DE]
- SCHWARZE, F. W.M.R.; SPYCHER, M.; FINK, S.: "Superior wood for violins - wood decay fungi a substitute for cold climate", NEW PHYTOLOGIST, vol. 179, 2008, pages 1095 - 1104, XP002611438, DOI: doi:10.1111/J.1469-8137.2008.02524.X
- HERRICK, F.W.; CASEBIER, R.L.; HAMILTON, J.K.; SANDBERG, K.R.: "Microfibrillated cellulose: Morphology and accessibility", J. APPL. POLYM. SCI. APPL. POLYM. SYMP., vol. 37, 1983, pages 797 - 813
- TURBAK, A.F.; SNYDER, F.W.; SANDBERG, K.R.: "Microfibrillated cellulose, a new cellulose product: Properties, uses, and commercial potential", J. APPL. POLYM. SCI. APPL. POLYM. SYMP., vol. 37, 1983, pages 815 - 827, XP009170845
- ANDRESEN, M.; JOHANSSON, L.S.; TANEM, B.S.; STENIUS, P.: "Properties and characterization of hydrophobized micro fibrillated cellulose", CELLULOSE, vol. 13, 2006, pages 665 - 677
- LU, J.; ASKELAND, P.; DRZAL, L.T.: "Surface modification of microfibrillated cellulose for epoxy composite applications", POLYMER, vol. 49, 2008, pages 1285 - 1298
- ZIMMERMANN, T.; PÖHLER, E.; GEIGER, T.: "Cellulose fibrils for polymer reinforcement", ADV. ENG. MAT., vol. 6, 2004, pages 754 - 761, XP002693417, DOI: doi:10.1002/adem.200400097
- IWAMOTO, S.; KAI, W.; ISOGAI, A.; IWATA, T.: "Elastic modulus of single cellulose microfibrils from tunicate measured by atomic force microscopy", BIOMACROMOLECULES, vol. 10, 2009, pages 2571 - 2576
- ANON: "The biotech Stradivarius", NATURE BIOTECHNOLOGY NEWS, vol. 28, 2009, pages 6
- BARLOW CY; EDWARDS PP; MILLWARD GR; RAPHAEL RA; RUBIO DJ: "Wood treatment used in Cremonese instruments", NATURE, vol. 332, 1988, pages 313
- BUCUR V: "Springer Series in Wood Science", 2006, SPRINGER, article "Acoustics of wood", pages: 407
- BURCKLE L; GRISSINO-MAYER HD: "Stradivaris, violins, tree rings, and the Maunder Minimum: a hypothesis", DENDROCHRONOLOGIA, vol. 21, 2003, pages 41 - 45, XP004959176, DOI: doi:10.1078/1125-7865-00033
- BURGERT I; FRÜHMANN K; KECKES J; FRATZL P; STANZL-TSCHEGG SE: "Microtensile Testing of Wood Fibers Combined with videextensometry for efficient Strain Detection", HOLZFORSCHUNG, vol. 57, no. 1, 2003, pages 661 - 664
- BRYNE .E; LAUSMAA J; ERNSTSSON M; ENGLUND F; WALLINDER MEP: "Ageing of modified wood. Part 2: Determination of surface composition of acetylated, furfurylated, and thermally modified wood by XPS and ToF-SIMS", HOLZFORSCHUNG, vol. 64, 2010, pages 305 - 313
- COSGROVE DJ: "Wall extensibility: its nature, measurement and relationship to plant cell growth", NEW PHYTOL, vol. 124, 1993, pages 1 - 23
- DIMIGEN H; DIMIGEN E, ZUM ALTERUNGSVERHALTEN VON TONHOLZ HOLZTECHNOLOGIE, vol. 1, 2014, pages 16 - 21
- ESPER J; COOK ER; SCHWEINGRUBER FH: "Low-frequency signals in long tree-ring chronologies for reconstructing past temperature variability", SCIENCE, vol. 295, 2002, pages 2250 - 2252
- EBRAHIMZADEH PR; KUBAT DG: "Effects of humidity changes on damping and stress relaxation in wood", J MATER SCI, vol. 28, 1993, pages 5668 - 5674
- GANNE-CHEDEVILLE C; ÄÄSKELÄNEN AS; FROIDEVAUX J; HUGHES M; NAVI P: "Natural and artificial ageing of spruce wood as observed by FTIR-ATR and UVR spectroscopy", HOLZFORSCHUNG, vol. 66, 2012, pages 163 - 170
- GARCIA ESTEBAN L; FERNANDEZ FG; CASASUS AG; DE PALACIOS P; GRIL J: "Comparison of the hygroscopic behaviour of 205-year-old and recently cut juvenile wood from *Pinus sylvestris* L", ANN FOR SCI, vol. 63, 2006, pages 309 - 317
- GUG R: "Choosing resonance wood", THE STRAD, vol. 102, 1991, pages 60 - 64
- HUNT DG; GRIL J: "Evidence of a physical ageing phenomenon in wood", J MATER SCI LETT, vol. 15, 1996, pages 80 - 92
- HOLZ D: "Untersuchungen an Resonanzhölzern. 1. Mitteilung: Beurteilung von Fichtenresonanzhölzern auf der Grundlage der Rohdichteverteilung und der Jahrringbreite", ARCHIV FÜR FORSTWESEN, vol. 15, 1966, pages 1287 - 1300
- JAKIELA S; BRATASZ L; KOZŁOWSKI R: "Numerical modeling of moisture movement and related stress field in lime wood subjected to changing climate conditions", WOOD SCI. TECHNOL., vol. 42, 2008, pages 21 - 37, XP019560072
- KATAOKA Y; KIGUCHI M: "Depth profiling of photo-induced degradation in wood by FT-IR microspectroscopy", J WOOD SCI, vol. 47, 2001, pages 325 - 327
- KÖHLER L; SPATZ HC: "Micromechanics of plant tissues beyond the linearelastic range", PLANTA, vol. 215, 2002, pages 33 - 40
- LEHRINGER C; KOCH G; ADUSUMALLI RB; MOOK WM; RICHTER K; MILITZ H: "Effect of *Physisporinus vitreus* on wood properties of Norway spruce. Part 1: aspects of delignification and surface hardness", HOLZFORSCHUNG, vol. 65, 2011, pages 711 - 719
- MATSUO M; YOKOYAMA M; UMEMURA K; SUGIYAMA J; KAWAI S; GRIL J; KUBODERA S; MITSUTANI T; OZAKI H; SAKAMOTO M: "ging of wood: analysis of color changes during natural aging and heat treatment", HOLZFORSCHUNG, vol. 65, 2011, pages 361 - 368

- MEYER HG: "A practical approach to the choice of tone wood for the instruments of the violin family", CATGUT ACOUSTICAL SOCIETY JOURNAL, vol. 2, 1995, pages 9 - 13
- MÜLLER HA: "Research Papers in Violin Acoustics: 1975-1993", vol. 1, 1986, USA: ACOUSTICAL SOCIETY OF AMERICA, article "How violin makers choose wood and what this procedure means from a physical point of view"
- NAGYVARY J; DIVERDI JA; OWEN O; DENNIS TOLLEY H: "Wood used by Stradivari and Guarneri", NATURE, vol. 444, 2006, pages 565
- NOGUCHI T; OBATAYA, E; ANDO K: "Effects of aging on the vibrational properties of wood", JOURNAL OF CULTURAL HERITAGE, vol. 13, 2012, pages 21 - 25
- ONO T; NORIMOTO M: "Study on Young's modulus and internal friction of wood in relation to the evaluation of wood for musical instruments", JAPAN JOURNAL OF APPLIED PHYSICS, vol. 22, 1983, pages 611 - 614
- ONO T; NORIMOTO M: "On physical criteria for the selection of wood for soundboards of musical instruments", RHEOL ACTA, vol. 23, 1984, pages 652 - 656
- PFRIEM A; EICHELBERGER K; WAGENFÜHR A: "Acoustic properties of thermally modified spruce for use of violins", J VIOLIN SOC AM, vol. 21, 2007, pages 102 - 111
- ROTH K: "Das chemische Geheimnis der Geigenvirtuosen Mit Stradivari, Kunstsaiten und Kolophonium", CHEM. UNSERER ZEIT, vol. 43, 2009, pages 168 - 181
- SCHLESKE M: "On the acoustical properties of violin varnish", CATGUT ACOUSTICAL SOCIETY JOURNAL, vol. 3, 1998, pages 15 - 24
- SCHMIDT, O; MORETH, U: "Characterization of indoor rot fungi byRAPD analysis", HOLZFORSCHUNG, vol. 52, 1998, pages 229 - 233
- SCHMIDT, O; MORETH, U: "Species-specific priming PCR in the rDNA-ITS region as a diagnostic tool for Serpula lacrymans", MYCOL. RESEARCH, vol. 104, 2000, pages 69 - 72, XP022454305, DOI: doi:10.1017/S0953756299001562
- SCHMIDT, O.; MORETH, U.: "Molekulare Untersuchungen an Hausfäulepilzen", ZEITSCHRIFT FÜR MYKOLOGIE, vol. 72, 2006, pages 137 - 152
- SCHWARZE FWMR; LONSDALE D; MATTHECK C: "Detectability of wood decay caused by Ustulina deusta in comparison with other tree-decay fungi", EUROPEAN JOURNAL OF FOREST PATHOLOGY, vol. 25, 1995, pages 327 - 341
- SCHWARZE FWMR; SPYCHER M; FINK S: "Superior wood for violins - wood decay fungi as a substitute for cold climate", NEW PHYTOLOGIST, vol. 179, 2008, pages 1095 - 1104, XP002611438, DOI: doi:10.1111/J.1469-8137.2008.02524.X
- SEDIGHI GILANI M; NAVI P.: "Experimental observations and micromechanical modeling of successive-damaging phenomenon in wood cells tensile behavior", WOOD SCI TECHNOL, vol. 41, no. 1, 2007, pages 69 - 85, XP019472204
- SEDIGHI GILANI, M.; BOONE, M.N.; MADER, K.; SCHWARZE, F.W.M.R.: "Synchrotron X-ray micro-tomography imaging and analysis of wood degraded by Physiporus vitreus and Xylaria longipes", JOURNAL OF STRUCTURAL BIOLOGY, vol. 187, 2014, pages 149 - 157
- SEDIGHI GILANI, M.; TINGAUT P.; HEEB M.; SCHWARZE, F.W.M.R.: "Influence of moisture on the vibro-mechanical properties of bio-engineered wood", JOURNAL OF MATERIAL SCIENCE, vol. 49, 2014, pages 7679 - 7687, XP035380366, DOI: doi:10.1007/s10853-014-8476-9
- SPYCHER M.: "The application of wood decay fungi to improve the acoustic properties of resonance wood for violins", PHD THESIS, 2008
- SPYCHER M; SCHWARZE FWMR; STEIGER R: "Assessment of resonance wood quality by comparing the physical and histological properties", WOOD SCIENCE AND TECHNOLOGY, vol. 42, 2008, pages 325 - 342, XP019585418
- STOEL BC; BORMAN TM: "Comparison of Wood Density between Classical Cremonese and Modern Violins", PLOS ONE, vol. 3, 2008, pages 1 - 7
- TOPHAM TJ; MCCORMICK MD: "A dendrochronological investigation of stringed instruments of the Cremonese School (1666-1757) including 'The Messiah' violin attributed to Antonio Stradivari", JOURNAL OF ARCHAEOLOGICAL SCIENCE, vol. 27, 2000, pages 183 - 192
- WAGENFÜHR A; PFRIEM A; EICHELBERGER K: "Der Einfluss einer thermischen Modifikation von Holz auf im Musikinstrumentenbau relevante Eigenschaften. Teil I: spezielle anatomische und physikalische Eigenschaften", HOLZTECHNOLOGIE, vol. 46, 2005, pages 36 - 42
- WAGENFÜHR A; PFRIEM A; EICHELBERGER K: "Der Einfluss einer thermischen Modifikation von Holz auf im Musikinstrumentenbau relevante Eigenschaften. Teil 2: technologische Eigenschaften, Herstellung und Prüfung von Musikinstrumentenbauteilen", HOLZTECHNOLOGIE, vol. 47, 2005, pages 39 - 43
- WEGST UGK: "Wood for sound", AMERICAN JOURNAL OF BOTANY, vol. 93, 2006, pages 1439 - 1448
- WHITE TJ; BRUNS T; LEE S; TAYLOR J: "PCR Protocols: a Guide to Methods and Applications", 1990, ACADEMIC PRESS, article "Amplification and direct sequencing of fungal ribosomal RNA genes for phylogenetics", pages: 315 - 321
- WINDEISEN E; BACHLE H; ZIMMER B; WEGENER G: "Relations between chemical changes and mechanical properties of thermally treated wood 10th EWLP, Stockholm, Sweden", HOLZFORSCHUNG, vol. 63, 2009, pages 773 - 778
- YANO H; KAJITA H; MINATO K: "Chemical treatment of wood for musical instruments", JOURNAL OF THE ACOUSTICAL SOCIETY OF AMERICA, vol. 96, 1994, pages 3380 - 3391, XP000482849, DOI: doi:10.1121/1.410600

Citation (search report)

- [AD] EP 1734504 A1 20061220 - SCHLESKE MARTIN [DE]
- [A] WO 2012056109 A2 20120503 - UPM KYMMENE CORP [FI], et al
- [XA] SCHWARZE FRANCIS W M R ET AL: "Superior wood for violins - wood decay fungi as a substitute for cold climate", NEW PHYTOLOGIST, CAMBRIDGE UNIVERSITY PRESS, CAMBRIDGE, GB, vol. 179, no. 4, 1 September 2008 (2008-09-01), pages 1095 - 1104, XP002611438, ISSN: 0028-646X, [retrieved on 20080628], DOI: 10.1111/J.1469-8137.2008.02524.X
- [A] FUHR M J ET AL: "Automated quantification of the impact of the wood-decay fungus on the cell wall structure of Norway spruce by tomographic microscopy", WOOD SCIENCE AND TECHNOLOGY ; JOURNAL OF THE INTERNATIONAL ACADEMY OF WOOD SCIENCE, SPRINGER, BERLIN, DE, vol. 46, no. 4, 26 August 2011 (2011-08-26), pages 769 - 779, XP035068957, ISSN: 1432-5225, DOI: 10.1007/S00226-011-0442-Y
- [A] LEHRINGER C ET AL: "Anatomy of bioincised Norway spruce wood", INTERNATIONAL BIODETERIORATION AND BIODEGRADATION, ELSEVIER LTD, GB, vol. 64, no. 5, 1 August 2010 (2010-08-01), pages 346 - 355, XP027067388, ISSN: 0964-8305, [retrieved on 20100601], DOI: 10.1016/J.IBIOD.2010.03.005
- [A] FRANZISKA GRÜNEBERGER ET AL: "Nanofibrillated cellulose in wood coatings: mechanical properties of free composite films", JOURNAL OF MATERIALS SCIENCE, vol. 49, no. 18, 18 June 2014 (2014-06-18), Dordrecht, pages 6437 - 6448, XP055304069, ISSN: 0022-2461, DOI: 10.1007/s10853-014-8373-2

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

EP 3232432 A1 20171018

DOCDB simple family (application)

EP 16164755 A 20160411