

Title (en)  
PART FOR CLOCK MOVEMENT

Title (de)  
BAUTEIL FÜR UHRWERK

Title (fr)  
PIÈCE POUR MOUVEMENT D'HORLOGERIE

Publication  
**EP 3273304 A1 20180124 (FR)**

Application  
**EP 16180226 A 20160719**

Priority  
EP 16180226 A 20160719

Abstract (en)  
[origin: US2018024503A1] The invention concerns the field of timepiece movements.

Abstract (fr)  
L'invention se rapporte à un composant horloger (1) comprenant au moins une partie (3) usinée par enlèvement de copeaux. Ladite partie (3) est réalisée en un alliage de cuivre amagnétique afin de limiter sa sensibilité aux champs magnétiques, ledit alliage de cuivre comprenant en poids entre 10% et 20% de Ni, entre 6% et 12% de Sn, X% d'éléments additionnels, où X est compris entre 0 et 5, et le reste de Cu. L'invention concerne le domaine des mouvements d'horlogerie.

IPC 8 full level  
**G04B 1/16** (2006.01); **G04B 13/02** (2006.01); **G04B 15/14** (2006.01); **G04B 17/32** (2006.01); **G04B 43/00** (2006.01)

CPC (source: CN EP RU US)  
**G04B 1/16** (2013.01 - CN EP US); **G04B 13/02** (2013.01 - EP US); **G04B 13/022** (2013.01 - US); **G04B 13/026** (2024.01 - CN); **G04B 15/14** (2013.01 - CN EP US); **G04B 17/32** (2013.01 - EP US); **G04B 29/00** (2013.01 - RU); **G04B 43/007** (2013.01 - EP US)

Citation (applicant)  
• FR 2015873 A1 19700430 - INST REINHARD STRAUMANN, et al  
• EP 2757423 A1 20140723 - OMEGA SA [CH]

Citation (search report)  
• [IY] EP 2860591 A1 20150415 - NIVAROX SA [CH]  
• [YD] EP 2757423 A1 20140723 - OMEGA SA [CH]  
• [A] EP 2437125 A1 20120404 - ROLEX SA [CH]  
• [A] CH 705464 A2 20130315 - NIVAROX SA [CH]  
• [AD] FR 2015873 A1 19700430 - INST REINHARD STRAUMANN, et al  
• [A] US 2004231159 A1 20041125 - SHIBUYA YOSHITSUGU [JP], et al  
• [A] AMETEK: "datasheet Pfinodal", 1 December 2010 (2010-12-01), pages 1 - 2, XP055350343, Retrieved from the Internet <URL:http://www.ametek-ct.com/pdf/tech/Pfinodal-ESC-Datasheet.pdf> [retrieved on 20170228]  
• [A] LAMINERIES MATTHEY SA: "BrushForm 158 / Toughmet 3", 1 June 2013 (2013-06-01), pages 1 - 3, XP055350340, Retrieved from the Internet <URL:http://www.matthey.ch/fileadmin/user\_upload/downloads/fichetechnique/EN/BF158\_T3\_C.pdf> [retrieved on 20170228]  
• [A] ANONYMOUS: "Materion Brush Performance Alloys Cold Rolled Temper Designations for BrushForm 158 Minimum 90° Bend Formability R/T Ratio Standard Designation ASTM Designation", MATERION, 1 January 2011 (2011-01-01), XP055289069, Retrieved from the Internet <URL:http://materion.com/~media/Files/PDFs/Alloy/DataSheets/Copper Nickel Tin Strip/Brushforms-DataSheets-Brushform158ColdRolled> [retrieved on 20160718]  
• [A] ROBERT E KUSNER ET AL: "Engineering Guide: ToughMet 3AT (C72900) ToughMet 3CX (C96900) Introduction", 2 October 2003 (2003-10-02), XP055350479, Retrieved from the Internet <URL:http://www.matthey.ch/fileadmin/user\_upload/downloads/Fichiers\_PDF/Toughmet\_Engin\_Guide.pdf> [retrieved on 20170301]

Cited by  
EP3885842A1; CH714594A1; WO2019145434A1; US11762338B2

Designated contracting state (EPC)  
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)  
BA ME

DOCDB simple family (publication)  
**EP 3273304 A1 20180124**; **EP 3273304 B1 20211110**; RU 2017125745 A 20190118; RU 2017125745 A3 20201116;  
RU 2017125759 A 20190121; RU 2017125759 A3 20201118; RU 2752467 C2 20210728; RU 2763382 C2 20211228; US 10761482 B2 20200901;  
US 2018024503 A1 20180125

DOCDB simple family (application)  
**EP 16180226 A 20160719**; RU 2017125745 A 20170718; RU 2017125759 A 20170718; US 201715652288 A 20170718