

Title (en)

METHOD FOR PRODUCING A HOT PRESS MEMBER

Title (de)

VERFAHREN ZUR HERSTELLUNG EINES HEISSPRESSELEMENT

Title (fr)

PROCÉDÉ DE PRODUCTION D'UN ÉLÉMENT DE PRESSE À CHAUD

Publication

EP 3366797 B1 20191218 (EN)

Application

EP 16857079 A 20161003

Priority

- JP 2015205751 A 20151019
- JP 2016004458 W 20161003

Abstract (en)

[origin: EP3366797A1] A hot pressed member having all of: high strength of 1500 MPa or more in tensile strength TS; high ductility of 6.0 % or more in uniform elongation uEl; and excellent heat treatment hardenability of increasing in yield stress YS by 150 MPa or more when subjected to heat treatment (baking finish) is provided. A hot pressed member comprises: a predetermined chemical composition (in particular, low C of 0.090 % or more and less than 0.30 % and high Mn of 3.5 % or more and less than 11.0 %); a microstructure including a martensite phase of 70.0 % or more in volume fraction and a retained austenite phase of 3.0 % or more and 30.0 % or less in volume fraction; and a dislocation density of 1.0×10^{16} /m² or more.

IPC 8 full level

C22C 38/00 (2006.01); **B21D 22/20** (2006.01); **C21D 1/18** (2006.01); **C21D 6/00** (2006.01); **C21D 8/02** (2006.01); **C21D 9/00** (2006.01); **C21D 9/46** (2006.01); **C22C 18/00** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01); **C22C 38/06** (2006.01); **C22C 38/08** (2006.01); **C22C 38/12** (2006.01); **C22C 38/14** (2006.01); **C22C 38/16** (2006.01); **C22C 38/18** (2006.01); **C22C 38/60** (2006.01); **C23C 2/02** (2006.01); **C23C 2/28** (2006.01); **C23C 2/40** (2006.01); **C23C 2/06** (2006.01); **C23C 2/12** (2006.01)

CPC (source: EP KR US)

B21D 22/20 (2013.01 - KR); **C21D 1/18** (2013.01 - EP US); **C21D 6/005** (2013.01 - EP US); **C21D 8/0205** (2013.01 - KR); **C21D 8/0226** (2013.01 - KR); **C21D 8/0236** (2013.01 - KR); **C21D 8/0263** (2013.01 - EP KR US); **C21D 8/0268** (2013.01 - EP US); **C21D 9/46** (2013.01 - EP US); **C22C 18/00** (2013.01 - EP US); **C22C 38/001** (2013.01 - EP US); **C22C 38/002** (2013.01 - EP US); **C22C 38/02** (2013.01 - EP KR US); **C22C 38/04** (2013.01 - EP KR US); **C22C 38/06** (2013.01 - EP KR US); **C22C 38/08** (2013.01 - EP US); **C22C 38/12** (2013.01 - EP US); **C22C 38/14** (2013.01 - EP US); **C22C 38/16** (2013.01 - EP US); **C22C 38/18** (2013.01 - EP US); **C23C 2/0224** (2022.08 - EP KR US); **C23C 2/024** (2022.08 - EP KR US); **C23C 2/06** (2013.01 - EP KR US); **C23C 2/12** (2013.01 - EP US); **C23C 2/28** (2013.01 - EP KR US); **C23C 2/40** (2013.01 - EP US); **C23C 30/005** (2013.01 - KR); **B21D 22/208** (2013.01 - EP US); **C21D 2211/001** (2013.01 - EP US); **C21D 2211/008** (2013.01 - EP KR US)

Citation (examination)

- US 2014065007 A1 20140306 - NAITOU JUNYA [JP], et al
- "PROPERTIES AND SELECTION : IRONS, STEELS & HIGH PERFORMANCE ALLOYS.", 31 March 1990, METALS PARK, OHIO : AMERICAN SOCIETY FOR METALS, US, ISBN: 978-0-87170-377-4, article N/A: "Metals Handbook: Properties and Selection: Irons, Steels & High Performance Alloys (Vol. 1, Edition 10)", pages: 146 - 147, XP055562279, 016775

Cited by

EP3438316A4; EP3492618A4; US11293075B2; US10858718B2

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)

EP 3366797 A1 20180829; **EP 3366797 A4 20180829**; **EP 3366797 B1 20191218**; CN 108138289 A 20180608; JP 2017078188 A 20170427; JP 6222198 B2 20171101; KR 20180063303 A 20180611; MX 2018004772 A 20180530; US 2019093191 A1 20190328; WO 2017068756 A1 20170427

DOCDB simple family (application)

EP 16857079 A 20161003; CN 201680061022 A 20161003; JP 2015205751 A 20151019; JP 2016004458 W 20161003; KR 20187013032 A 20161003; MX 2018004772 A 20161003; US 201615768894 A 20161003