

Title (en)  
SPECIAL BRASS ALLOY PRODUCT AND METHOD FOR ITS PRODUCTION

Title (de)  
SONDERMESSINGLEGIERUNGS-PRODUKT UND VERFAHREN ZU DESSEN HERSTELLUNG

Title (fr)  
PRODUIT EN ALLIAGE DE LAITON COMPLEXE ET PROCÉDÉ DE SA PRODUCTION

Publication  
**EP 3368701 A1 20180905 (DE)**

Application  
**EP 17751673 A 20170727**

Priority  
• DE 202016104552 U 20160819  
• DE 202016105310 U 20160923  
• EP 2017069001 W 20170727

Abstract (en)  
[origin: WO2018033360A1] The invention relates to a special brass alloy product comprising 62 – 68 wt.% Cu, 0.2 – 2.2 wt.% Fe, 5.5 – 9.0 wt.% Mn, 3.5 – 7.5 wt.% Al, 0.6 – 2.5 wt.% Si, max. 0.7 wt.% Sn, max. 0.7 wt.% Ni, max. 0.1 wt.% Pb, with the rest being Zn together with unavoidable impurities, and having a portion of  $\alpha$ -phase between 15% and 40%. The invention also relates to a method for producing a special brass alloy product of this type, wherein, in a first step, a semi-finished product is produced from a blank with at least one hot forming step, and wherein the semi-finished product is subsequently subjected to a heat treatment between 300°C and 450°C for 3 to 12 hours, in order to form the  $\alpha$ -phase portion.

IPC 8 full level  
**C22C 9/04** (2006.01); **C22F 1/08** (2006.01); **F01L 3/08** (2006.01); **F16C 33/12** (2006.01)

CPC (source: EP)  
**C22C 9/04** (2013.01); **C22F 1/08** (2013.01); **F01L 3/08** (2013.01); **F01L 2301/00** (2020.05); **F01L 2303/00** (2020.05); **F01L 2820/01** (2013.01); **F16C 33/121** (2013.01); **F16C 2204/14** (2013.01)

Citation (search report)  
See references of WO 2018033360A1

Designated contracting state (EPC)  
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)  
BA ME

DOCDB simple family (publication)  
**WO 2018033360 A1 20180222**; EP 3368701 A1 20180905

DOCDB simple family (application)  
**EP 2017069001 W 20170727**; EP 17751673 A 20170727