

Title (en)
AUSTENITIC STAINLESS STEEL

Title (de)
AUSTENITISCHER EDELSTAHL

Title (fr)
ACIER INOXYDABLE AUSTÉNITIQUE

Publication
EP 3480330 A4 20200108 (EN)

Application
EP 17820177 A 20170628

Priority
• JP 2016128321 A 20160629
• JP 2017023657 W 20170628

Abstract (en)
[origin: EP3480330A1] Provided is an austenitic stainless steel having excellent anti-carburizing properties even in a high temperature carburizing environment, and an excellent hot workability in its production. The austenitic stainless steel according to the present embodiment includes a chemical composition consisting of, in mass percent, C: 0.03 to less than 0.25%, Si: 0.01 to 2.0%, Mn: 2.0% or less, Cr: 10 to less than 22%, Ni: more than 30.0% to 40.0%, Al: more than 2.5% to less than 4.5%, Nb: 0.01 to 3.5%, Ca: 0.0005 to 0.05%, Mg: 0.0005 to 0.05%, and N: 0.03% or less, with the balance being Fe and impurities. In the austenitic stainless steel, a Cr concentration C_{Cr}' in its outer layer and an Al concentration C_{Al}' in the outer layer satisfy Formula (1) for a Cr concentration C_{Cr} in an other-than-outer-layer region and an Al concentration C_{Al} in the other-than-outer-layer region. $0.40 \leq C_{Cr} \cdot C_{Al} / C_{Cr}' \cdot C_{Al}' \leq 0.80$

IPC 8 full level
C22C 38/48 (2006.01); **C21D 6/00** (2006.01); **C21D 8/00** (2006.01); **C21D 8/02** (2006.01); **C21D 8/10** (2006.01); **C21D 9/08** (2006.01); **C21D 9/46** (2006.01); **C22C 38/00** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01); **C22C 38/06** (2006.01); **C22C 38/34** (2006.01); **C22C 38/42** (2006.01); **C22C 38/44** (2006.01); **C22C 38/46** (2006.01); **C22C 38/50** (2006.01); **C22C 38/54** (2006.01); **C22C 38/58** (2006.01)

CPC (source: EP KR US)
C21D 6/00 (2013.01 - EP US); **C21D 6/004** (2013.01 - EP); **C21D 8/00** (2013.01 - EP US); **C21D 8/0236** (2013.01 - EP); **C21D 8/0268** (2013.01 - EP); **C21D 8/10** (2013.01 - EP US); **C21D 8/105** (2013.01 - EP); **C21D 9/08** (2013.01 - EP); **C21D 9/46** (2013.01 - EP); **C22C 30/02** (2013.01 - US); **C22C 38/00** (2013.01 - EP US); **C22C 38/001** (2013.01 - EP US); **C22C 38/002** (2013.01 - EP US); **C22C 38/02** (2013.01 - EP US); **C22C 38/04** (2013.01 - EP US); **C22C 38/06** (2013.01 - EP US); **C22C 38/34** (2013.01 - EP US); **C22C 38/42** (2013.01 - EP KR US); **C22C 38/44** (2013.01 - EP KR US); **C22C 38/46** (2013.01 - EP KR US); **C22C 38/48** (2013.01 - EP US); **C22C 38/50** (2013.01 - EP KR US); **C22C 38/54** (2013.01 - EP US); **C22C 38/58** (2013.01 - EP KR US); **C21D 8/105** (2013.01 - US); **C21D 2211/001** (2013.01 - EP KR US)

Citation (search report)
• [I] JP H06264193 A 19940920 - SUMITOMO METAL IND
• [A] US 2013266477 A1 20131010 - YAMAMOTO YUKINORI [US], et al
• [A] JP S5923855 A 19840207 - NIPPON KOKAN KK
• [A] WO 2015038406 A1 20150319 - EATON CORP [US]
• [A] US 2008304996 A1 20081211 - BRADY MICHAEL P [US], et al
• [A] US 5660938 A 19970826 - SATO KOJI [US], et al
• See references of WO 2018003823A1

Cited by
SE2150122A1; SE543920C2

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)
EP 3480330 A1 20190508; EP 3480330 A4 20200108; CA 3028610 A1 20180104; CN 109415786 A 20190301; JP 6614347 B2 20191204; JP WO2018003823 A1 20190425; KR 102124914 B1 20200619; KR 20190022723 A 20190306; SG 11201810839T A 20190130; US 2019127832 A1 20190502; WO 2018003823 A1 20180104

DOCDB simple family (application)
EP 17820177 A 20170628; CA 3028610 A 20170628; CN 201780040380 A 20170628; JP 2017023657 W 20170628; JP 2018525193 A 20170628; KR 20197002265 A 20170628; SG 11201810839T A 20170628; US 201716310613 A 20170628