

Title (en)

THIN SHEETS MADE OF AN ALUMINIUM-MAGNESIUM-SCANDIUM ALLOY FOR AEROSPACE APPLICATIONS

Title (de)

DÜNNE BLECHE AUS ALUMINIUM-MAGNESIUM-SCANDIUM-LEGIERUNG FÜR ANWENDUNGEN IN DER LUFT- UND RAUMFAHRT

Title (fr)

TOLES MINCES EN ALLIAGE ALUMINIUM-MAGNESIUM-SCANDIUM POUR APPLICATIONS AEROSPATIALES

Publication

EP 3526358 A1 20190821 (FR)

Application

EP 17794387 A 20171017

Priority

- FR 1660049 A 20161017
- FR 2017052856 W 20171017

Abstract (en)

[origin: CA3037115A1] The invention relates to a method for producing a hot-worked product made of an aluminium alloy composed, in wt%, of Mg: 3.8-4.2; Mn: 0.3-0.8 and preferably 0.5-0.7, Sc: 0.1-0.3; Zn: 0.1-0.4; Ti: 0.01-0.05; Zr: 0.07-0.15; Cr: <0.01; Fe: <0.15; Si <0.1; wherein the homogenisation is carried out at a temperature of between 370°C and 450°C, for between 2 and 50 hours, such that the equivalent time at 400°C is between 5 and 100 hours, and the hot deformation is carried out at an initial temperature of between 350°C and 450°C. The invention also relates to hot-worked products obtained by the method according to the invention, in particular sheets with a thickness of less than 12mm. The products according to the invention are advantageous as they offer a better compromise in terms of mechanical strength, toughness and hot-formability.

IPC 8 full level

C22C 21/06 (2006.01); **C22F 1/047** (2006.01)

CPC (source: EP US)

C22C 21/06 (2013.01 - EP US); **C22F 1/047** (2013.01 - EP US)

Citation (search report)

See references of WO 2018073533A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

FR 3057476 A1 20180420; **FR 3057476 B1 20181012**; BR 112019006323 A2 20190625; CA 3037115 A1 20180426; CN 109844151 A 20190604; CN 109844151 B 20210319; EP 3526358 A1 20190821; EP 3526358 B1 20200722; US 2019249285 A1 20190815; US 2023151473 A1 20230518; WO 2018073533 A1 20180426

DOCDB simple family (application)

FR 1660049 A 20161017; BR 112019006323 A 20171017; CA 3037115 A 20171017; CN 201780064272 A 20171017; EP 17794387 A 20171017; FR 2017052856 W 20171017; US 201716342096 A 20171017; US 202318156074 A 20230118