

Title (en)
HIGH-STRENGTH STEEL PLATE FOR SOUR RESISTANT LINE PIPE, METHOD FOR MANUFACTURING SAME, AND HIGH-STRENGTH STEEL PIPE USING HIGH-STRENGTH STEEL PLATE FOR SOUR RESISTANT LINE PIPE

Title (de)
HOCHFESTE STAHLPLATTE FÜR SAUER GASBESTÄNDIGES LEITUNGSROHR, VERFAHREN ZUR HERSTELLUNG DAVON UND HOCHFESTES STAHLROHR MIT HOCHFESTEM STAHLBLECH FÜR SAUER GASBESTÄNDIGES LEITUNGSROHR

Title (fr)
PLAQUE D'ACIER HAUTE RÉISTANCE POUR TUYAU DE CANALISATION RÉISTANT À L'ACIDITÉ, SON PROCÉDÉ DE FABRICATION, ET TUYAU EN ACIER HAUTE RÉISTANCE UTILISANT UNE PLAQUE D'ACIER HAUTE RÉISTANCE POUR TUYAU DE CANALISATION RÉISTANT À L'ACIDITÉ

Publication
EP 3604584 A4 20200304 (EN)

Application
EP 17903712 A 20170926

Priority
• JP 2017013405 W 20170330
• JP 2017034800 W 20170926

Abstract (en)
[origin: EP3604584A1] Disclosed is a high strength steel plate for a sour-resistant line pipe that is excellent not only in HIC resistance but also in SSCC resistance under more severe corrosion environments. The high strength steel plate for a sour-resistant line pipe has: a chemical composition containing, by mass%, C: 0.02 % to 0.08 %, Si: 0.01 % to 0.50 %, Mn: 0.50 % to 1.80 %, P: 0.001 % to 0.015 %, S: 0.0002 % to 0.0015 %, Al: 0.01 % to 0.08 %, and Ca: 0.0005 % to 0.005 %, with the balance being Fe and inevitable impurities; a steel microstructure at 0.5 mm below a surface of the steel plate being a bainite microstructure having a dislocation density of 1.0×10^{14} to $7.0 \times 10^{14} \text{ (m}^{-2}\text{)}$; a variation in Vickers hardness at 0.5 mm below the surface of the steel plate being 30 HV or less at 3σ , where σ is a standard deviation; and a tensile strength being 520 MPa or more.

IPC 8 full level
C22C 38/00 (2006.01); **C21D 8/02** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01); **C22C 38/06** (2006.01); **C22C 38/58** (2006.01)

CPC (source: EP KR)
C21D 1/02 (2013.01 - EP); **C21D 1/19** (2013.01 - EP); **C21D 8/02** (2013.01 - EP KR); **C21D 8/0263** (2013.01 - EP); **C21D 9/08** (2013.01 - EP); **C21D 9/085** (2013.01 - EP); **C21D 9/46** (2013.01 - EP); **C22C 38/02** (2013.01 - EP); **C22C 38/04** (2013.01 - EP KR); **C22C 38/06** (2013.01 - EP KR); **C22C 38/58** (2013.01 - KR); **C21D 6/005** (2013.01 - EP); **C21D 8/0231** (2013.01 - EP); **C22C 38/00** (2013.01 - EP); **C22C 38/12** (2013.01 - EP); **C22C 38/14** (2013.01 - EP); **C22C 38/16** (2013.01 - EP); **C22C 38/18** (2013.01 - EP); **C22C 38/20** (2013.01 - EP); **C22C 38/24** (2013.01 - EP); **C22C 38/26** (2013.01 - EP); **C22C 38/28** (2013.01 - EP); **C22C 38/58** (2013.01 - EP)

Citation (search report)
• [X] EP 2617853 A1 20130724 - JFE STEEL CORP [JP]
• [A] JP 2012077331 A 20120419 - JFE STEEL CORP
• [A] JP 5991174 B2 20160914
• [A] EP 2728029 A1 20140507 - JFE STEEL CORP [JP]
• [A] EP 2617851 A1 20130724 - JFE STEEL CORP [JP]
• See references of WO 2018179512A1

Cited by
US12037667B2; EP3859027A4; EP3859026A4

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)
BA ME

DOCDB simple family (publication)
EP 3604584 A1 20200205; **EP 3604584 A4 20200304**; **EP 3604584 B1 20220518**; BR 112019019696 A2 20200414; BR 112019019696 B1 20220719; CN 110462080 A 20191115; CN 110462080 B 20220104; JP 6521197 B2 20190529; JP WO2018179512 A1 20190418; KR 102478368 B1 20221215; KR 20190129957 A 20191120; KR 20210118961 A 20211001; WO 2018179512 A1 20181004

DOCDB simple family (application)
EP 17903712 A 20170926; BR 112019019696 A 20170926; CN 201780089150 A 20170926; JP 2017034800 W 20170926; JP 2018564992 A 20170926; KR 20197030659 A 20170926; KR 20217029889 A 20170926