

Title (en)

METHOD AND DEVICE FOR INSERTING A SEPARATION LINE INTO A TRANSPARENT, BRITTLE-FRACTURE MATERIAL, AND ELEMENT THAT CAN BE PRODUCED ACCORDING TO THE METHOD AND IS PROVIDED WITH A SEPARATION LINE

Title (de)

VERFAHREN UND VORRICHTUNG ZUM EINFÜGEN EINER TRENNLINIE IN EIN TRANSPARENTE SPRÖDBRÜCHIGES MATERIAL, SOWIE VERFAHRENSGEMÄSS HERSTELLBARES, MIT EINER TRENNLINIE VERSEHENES ELEMENT

Title (fr)

PROCÉDÉ ET DISPOSITIF POUR INSÉRER UNE LIGNE DE SÉPARATION DANS UN MATÉRIAUX TRANSPARENT CASSANT, AINSI QU'ÉLÉMENT POURVU D'UNE LIGNE DE SÉPARATION, POUVANT ÊTRE FABRIQUÉ SELON LE PROCÉDÉ

Publication

EP 3752314 A1 20201223 (DE)

Application

EP 19705160 A 20190211

Priority

- DE 102018103456 A 20180215
- DE 102018126381 A 20181023
- EP 2019053344 W 20190211

Abstract (en)

[origin: WO2019158488A1] The aim of the invention is that of preparing a brittle-fracture, transparent substrate for a separation process and creating a prepared separation line along which the element can be separated without high breaking forces and without the associated risk of conchoidal fractures on the produced edge. To this end, the invention proposes a method for preparing a parting of a workpiece (2), in which - a workpiece (2) is provided that is transparent for the light of a pulsed laser beam (4), wherein - the laser beam (4) is split into at least two partial beams (41, 42) by means of an optical system (6), wherein both partial beams (41, 42) are directed onto the workpiece (2) in such a way that they strike the workpiece (2) at different angles to the normal of the irradiated surface (21) and are superimposed in the interior of the workpiece (2), and the partial beams (41, 42) interfere with each other in such a way that a sequence of intensity maximums (45) lined up one after the other along the overlapping region (43) of the partial beams (41, 42) in the interior of the workpiece is formed, and wherein the intensity in the intensity maximums (45) is so high that the material of the workpiece (2) is modified such that a chain-like periodic arrangement (9) of material modifications (8) is formed, and wherein the workpiece (2) and the partial beams (41, 42) are moved relative to one another such that a plurality of chain-like periodic arrangements (9) of material modifications (8) along a path forming a separation line are produced.

IPC 8 full level

B23K 26/06 (2014.01); **B23K 26/0622** (2014.01); **B23K 26/067** (2006.01); **B23K 26/073** (2006.01); **B23K 26/08** (2014.01); **B23K 26/53** (2014.01); **C03B 33/02** (2006.01); **B23K 103/00** (2006.01)

CPC (source: EP KR US)

B23K 26/0608 (2013.01 - EP KR); **B23K 26/0613** (2013.01 - EP KR); **B23K 26/0622** (2015.10 - US); **B23K 26/0624** (2015.10 - EP KR); **B23K 26/0648** (2013.01 - EP KR); **B23K 26/067** (2013.01 - US); **B23K 26/0676** (2013.01 - EP KR); **B23K 26/0736** (2013.01 - EP KR); **B23K 26/08** (2013.01 - EP KR); **B23K 26/359** (2015.10 - US); **B23K 26/53** (2015.10 - EP KR); **C03B 33/0222** (2013.01 - EP KR); **B23K 26/0648** (2013.01 - US); **B23K 2103/52** (2018.08 - EP KR US); **B23K 2103/54** (2018.08 - EP KR US); **Y02P 40/57** (2015.11 - EP)

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

WO 2019158488 A1 20190822; CN 111699070 A 20200922; CN 111699070 B 20220916; DE 102018126381 A1 20190822; EP 3752314 A1 20201223; JP 2021513951 A 20210603; JP 2023036745 A 20230314; JP 7198285 B2 20221228; JP 7495471 B2 20240604; KR 102605322 B1 20231122; KR 20200119322 A 20201019; US 2020376603 A1 20201203

DOCDB simple family (application)

EP 2019053344 W 20190211; CN 201980012585 A 20190211; DE 102018126381 A 20181023; EP 19705160 A 20190211; JP 2020543638 A 20190211; JP 2022200984 A 20221216; KR 20207026499 A 20190211; US 202016994724 A 20200817