

Title (en)

POLYPROPYLENE COMPOSITION AND MOLDED ARTICLE

Title (de)

POLYPROPYLENZUSAMMENSETZUNG UND FORMARTIKEL

Title (fr)

COMPOSITION DE POLYPROPYLÈNE ET ARTICLE MOULÉ

Publication

EP 3765534 A1 20210120 (EN)

Application

EP 19717372 A 20190315

Priority

- JP 2018050028 A 20180316
- JP 2019012288 W 20190315

Abstract (en)

[origin: WO2019177180A1] The present invention provides a polypropylene composition having an excellent balance between transparency and flexibility. A polypropylene composition comprising: as component (1), a propylene/ethylene copolymer containing 2 to 4% by weight of an ethylene-derived unit; and as component (2), an ethylene/propylene copolymer containing 65 to 87% by weight of an ethylene-derived unit; wherein the polypropylene composition satisfies the following requirements: 1) the weight ratio of component (1) to component (2) is in the range of 65:35 to 77:23, 2) the intrinsic viscosity of xylene solubles (XSIV) of the composition is in the range of 0.8 to 1.4 dl/g, 3) the MFR (at 230°C under a load of 2.16 kg) of the composition is in the range of 15 to 40 g/10 min., 4) no crystal nucleating agent is contained.

IPC 8 full level

C08F 210/06 (2006.01); **C08F 210/16** (2006.01)

CPC (source: EP US)

C08F 210/06 (2013.01 - EP); **C08L 23/14** (2013.01 - EP US)

Citation (search report)

See references of WO 2019177180A1

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

WO 2019177180 A1 20190919; WO 2019177180 A8 20191226; BR 112020017766 A2 20201222; CN 111741987 A 20201002;
EP 3765534 A1 20210120; JP 2019157084 A 20190919; JP 7096682 B2 20220706; US 11306198 B2 20220419; US 2020407540 A1 20201231

DOCDB simple family (application)

JP 2019012288 W 20190315; BR 112020017766 A 20190315; CN 201980014042 A 20190315; EP 19717372 A 20190315;
JP 2018050028 A 20180316; US 201916981092 A 20190315