

Title (en)

ALLOY FOR USE IN A SACRIFICIAL ANODE AND A SACTIFICIAL ANODE

Title (de)

LEGIERUNG ZUR VERWENDUNG IN EINER OPFERANODE UND OPFERANODE

Title (fr)

ALLIAGE DESTINÉ À ÊTRE UTILISÉ DANS UNE ANODE SACRIFICIELLE ET ANODE SACRIFICIELLE

Publication

**EP 3835441 A1 20210616 (EN)**

Application

**EP 19215052 A 20191210**

Priority

EP 19215052 A 20191210

Abstract (en)

The present invention relates to an aluminium-based alloy for use in a sacrificial anode and a sacrificial anode produced from the aluminium-based alloy. The aluminium-based alloy comprises: maximum 0.5% by weight of zinc, maximum 0.04% by weight of indium, maximum 0.1% by weight of gallium, maximum 0.08% by weight of iron, maximum 0.003% by weight of copper, elements in form of impurities in an amount of maximum 0.02% by weight of each element, and balance aluminium. The alloy has a high electrochemical efficiency and a low potential and provides good properties in respect of cathodic protection.

IPC 8 full level

**C22C 21/10** (2006.01); **C23F 13/14** (2006.01)

CPC (source: EP)

**C22C 21/10** (2013.01); **C23F 13/14** (2013.01); **C23F 2213/31** (2013.01)

Citation (search report)

- [X1] US 2013084208 A1 20130404 - MISRA ABHIJEET [US], et al
- [A] US 4885045 A 19891205 - MAY ROBIN F [AU]
- [A] ANSHUMAN SHARMA ET AL: "and thermodynamic modelling of alloying effects on activity of sacrificial aluminium anodes", CORROSION SCIENCE, OXFORD, GB, vol. 53, no. 5, 20 January 2011 (2011-01-20), pages 1724 - 1731, XP028156793, ISSN: 0010-938X, [retrieved on 20110128], DOI: 10.1016/J.CORSCI.2011.01.046

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

**EP 3835441 A1 20210616**; EP 3835442 A1 20210616

DOCDB simple family (application)

**EP 19215052 A 20191210**; EP 20204306 A 20201028