

Title (en)

FOUNDRIY ALLOYS FOR HIGH-PRESSURE VACUUM DIE CASTING

Title (de)

GIESSEREILEGIERUNGEN ZUM HOCHDRUCKVAKUUMGIESSEN

Title (fr)

ALLIAGES DE FONDERIE DESTINÉS AU COULAGE SOUS VIDE À HAUTE PRESSION

Publication

EP 3914747 A1 20211201 (EN)

Application

EP 20744830 A 20200124

Priority

- US 201962796735 P 20190125
- CA 2020050082 W 20200124

Abstract (en)

[origin: WO2020150830A1] The present disclosure concerns a cast aluminum alloy for making cast aluminum products, especially using high-pressure vacuum die casting operations. The cast aluminum alloy comprises, in weight percent: Ni between about 1.5 and about 6.5; Si between about 0.10 and 1.5; Mg between about 0.10 and about 3; Fe up to about 0.2; Mn up to about 0.65; Ti up to about 0.12; V up to about 0.15; Zr up to about 0.15; Mo up to about 0.15; Cr up to about 0.01; Sr up to about 0.02; and the balance being aluminum and unavoidable impurities.

IPC 8 full level

C22C 21/00 (2006.01); **C22C 21/02** (2006.01); **C22C 21/04** (2006.01); **C22C 21/08** (2006.01)

CPC (source: EP KR US)

B22D 21/007 (2013.01 - KR); **B22D 21/04** (2013.01 - EP); **C22C 21/00** (2013.01 - EP KR US); **C22C 21/08** (2013.01 - EP); **C22F 1/04** (2013.01 - EP US); **C22F 1/047** (2013.01 - EP)

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

WO 2020150830 A1 20200730; CA 3125339 A1 20200730; EP 3914747 A1 20211201; EP 3914747 A4 20221102; JP 2022517830 A 20220310; KR 20210118852 A 20211001; MX 2021008718 A 20210824; US 2022090234 A1 20220324

DOCDB simple family (application)

CA 2020050082 W 20200124; CA 3125339 A 20200124; EP 20744830 A 20200124; JP 2021542121 A 20200124; KR 20217025030 A 20200124; MX 2021008718 A 20200124; US 202017425443 A 20200124