

Title (en)
PROCESS FOR MANUFACTURING AN ALUMINUM ALLOY PART

Title (de)
VERFAHREN ZUR HERSTELLUNG EINES ALUMINIUMLEGIERUNGSTEILS

Title (fr)
PROCEDE DE FABRICATION D'UNE PIÈCE EN ALLIAGE D'ALUMINIUM

Publication
EP 3924123 A1 20211222 (FR)

Application
EP 20710219 A 20200213

Priority
• FR 1901575 A 20190215
• FR 1911356 A 20191011
• FR 2020050266 W 20200213

Abstract (en)
[origin: WO2020165542A1] The invention relates to a method for manufacturing a part (20) comprising a formation of successive metal layers (201... 20n) superposed on one another, each layer being formed by depositing a filler metal (15, 25), energy being supplied to the filler metal in such a way that it melts and, upon solidification, constitutes said layer, the method being characterized in that the filler metal (15, 25) is an aluminum alloy comprising the following alloying elements (in wt %): Zr: 0.5% to 2.5%, preferably, according to a first variant, 0.8 to 2.5%, more preferably 1 to 2.5%, even more preferably 1.3 to 2.5%; or preferably, according to a second variant, 0.5 to 2%, more preferably 0.6 to 1.8%, more preferably 0.6 to 1.6%, more preferably 0.7 to 1.5%, more preferably 0.8 to 1.5%, more preferably 0.9 to 1.5%, even more preferably 1 to 1.4%; Fe: 0% to 3%, preferably 0.5 to 2.5%; preferably, according to a first variant, 0.8 to 2.5%, preferably 0.8 to 2%, more preferably 0.8 to 1.2%; or preferably, according to a second variant, 1.5 to 2.5%, preferably 1.6 to 2.4%, more preferably 1.7 to 2.3%; optionally Si: $\leq 0.3\%$, preferably $\leq 0.2\%$, more preferably $\leq 0.1\%$; optionally Cu: $\leq 0.5\%$, preferably 0.05 to 0.5%, preferably 0.1 to 0.4%; optionally Mg: $\leq 0.2\%$, preferably $\leq 0.1\%$, preferably $< 0.05\%$; other alloying elements: $< 0.1\%$ individually, and in total $< 0.5\%$; impurities: $< 0.05\%$ individually, and in total $< 0.15\%$; the remainder being aluminum.

IPC 8 full level
B22F 3/105 (2006.01); **B22F 1/06** (2022.01); **B33Y 10/00** (2015.01); **B33Y 70/00** (2020.01); **B33Y 80/00** (2015.01); **C22C 1/04** (2006.01); **C22C 21/00** (2006.01); **C22F 1/04** (2006.01)

CPC (source: EP US)
B22F 1/06 (2022.01 - EP US); **B22F 3/105** (2013.01 - EP); **B22F 10/64** (2021.01 - EP US); **B23K 26/342** (2015.10 - US); **B33Y 10/00** (2014.12 - EP US); **B33Y 40/20** (2020.01 - EP US); **B33Y 70/00** (2014.12 - EP US); **B33Y 80/00** (2014.12 - EP); **C22C 1/0416** (2013.01 - EP US); **C22C 21/00** (2013.01 - EP US); **C22F 1/04** (2013.01 - EP US); **B22F 3/15** (2013.01 - EP); **B22F 9/082** (2013.01 - EP); **B22F 10/25** (2021.01 - EP US); **B22F 10/28** (2021.01 - EP US); **B22F 10/36** (2021.01 - EP US); **B22F 10/364** (2021.01 - EP US); **B22F 2003/1051** (2013.01 - EP); **B22F 2003/248** (2013.01 - EP); **B22F 2301/052** (2013.01 - US); **B22F 2998/10** (2013.01 - EP); **B23K 2103/10** (2018.08 - US); **Y02P 10/25** (2015.11 - EP)

C-Set (source: EP US)
1. **B22F 2998/10 + B22F 10/28 + B22F 3/162 + B22F 2003/248 + B22F 3/15**
2. **B22F 2998/10 + B22F 10/25 + B22F 3/162 + B22F 2003/248 + B22F 3/15**
3. **B22F 2998/10 + B22F 10/25 + B22F 3/15 + B22F 2003/248**
4. **B22F 2998/10 + B22F 10/28 + B22F 3/15 + B22F 2003/248**

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)
BA ME

DOCDB simple family (publication)
WO 2020165542 A1 20200820; CN 113412172 A 20210917; CN 113412172 B 20240430; CN 113423524 A 20210921; CN 113423524 B 20240312; EP 3924123 A1 20211222; EP 3924124 A1 20211222; EP 3924124 B1 20231115; FR 3092776 A1 20200821; FR 3092776 B1 20220923; FR 3092777 A1 20200821; US 2022213579 A1 20220707

DOCDB simple family (application)
FR 2020050264 W 20200213; CN 202080013589 A 20200213; CN 202080013752 A 20200213; EP 20710219 A 20200213; EP 20711231 A 20200213; FR 1901575 A 20190215; FR 1911356 A 20191011; US 202017430650 A 20200213