

Title (en)

POLYHYDROXY ALKANOATE RESIN COMPOSITION, MOLDED ARTICLE THEREOF, AND FILM OR SHEET

Title (de)

POLYHYDROXYALKANOATHARZZUSAMMENSETZUNG, FORMARTIKEL DARAUS UND FILM ODER FOLIE

Title (fr)

COMPOSITION DE RÉSINE DE POLYHYDROXYALCANOATE, ARTICLE MOULÉ CORRESPONDANT ET FILM OU FEUILLE

Publication

EP 3950838 A1 20220209 (EN)

Application

EP 20777429 A 20200228

Priority

- JP 2019062424 A 20190328
- JP 2020008440 W 20200228

Abstract (en)

Provided is a polyhydroxyalkanoate resin composition containing a polyhydroxyalkanoate resin component. In differential scanning calorimetry of the resin composition, a highest melting peak temperature is 130 °C or higher, and a total crystalline melting enthalpy calculated from all melting peaks is in the range of 20 to 65 J/g. Preferably, the polyhydroxyalkanoate resin component is a mixture of at least two polyhydroxyalkanoate resins differing in crystalline melting enthalpy.

IPC 8 full level

C08L 67/04 (2006.01); **C08G 63/06** (2006.01)

CPC (source: EP US)

C08G 63/06 (2013.01 - EP); **C08J 5/18** (2013.01 - EP US); **C08L 67/04** (2013.01 - EP US); **C08J 2367/04** (2013.01 - EP US); **C08J 2467/04** (2013.01 - EP US); **C08L 2203/16** (2013.01 - US); **C08L 2205/025** (2013.01 - EP US); **C08L 2205/03** (2013.01 - US)

C-Set (source: EP)

1. **C08L 67/04 + C08L 67/04**
2. **C08L 67/04 + C08L 67/04 + C08K 3/36**
3. **C08L 67/04 + C08L 67/04 + C08K 3/36 + C08K 5/103**

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

DOCDB simple family (publication)

EP 3950838 A1 20220209; **EP 3950838 A4 20221228**; CN 113631657 A 20211109; CN 113631657 B 20240315; JP WO2020195550 A1 20201001; US 2022041823 A1 20220210; WO 2020195550 A1 20201001

DOCDB simple family (application)

EP 20777429 A 20200228; CN 202080022584 A 20200228; JP 2020008440 W 20200228; JP 2021508867 A 20200228; US 202117480335 A 20210921