

Title (en)
FREE-CUTTING COPPER ALLOY CASTING, AND METHOD FOR PRODUCING FREE-CUTTING COPPER ALLOY CASTING

Title (de)
KUPFERAUTOMATENLEGIERUNGSGUSS UND VERFAHREN ZUR HERSTELLUNG DES KUPFERAUTOMATENLEGIERUNGSGUSSES

Title (fr)
PIÈCE COULÉE EN ALLIAGE DE CUIVRE POUR DÉCOLLETAGE, ET PROCÉDÉ DE PRODUCTION DE PIÈCE COULÉE EN ALLIAGE DE CUIVRE POUR DÉCOLLETAGE

Publication
EP 3992321 A4 20230809 (EN)

Application
EP 20831431 A 20200217

Priority

- JP 2019116914 A 20190625
- JP 2019130143 A 20190712
- JP 2019141096 A 20190731
- JP 2019163773 A 20190909
- JP 2019048455 W 20191211
- JP 2020006037 W 20200217
- JP 2019048438 W 20191211
- JP 2019050255 W 20191223

Abstract (en)
[origin: EP3992321A1] This copper alloy casting includes, in terms of mass%: Cu: higher than 58.5% and lower than 65.0%; Si: higher than 0.40% and lower than 1.40%; Pb: higher than 0.002% and lower than 0.25%; P: higher than 0.003% and lower than 0.19%; and Bi: 0.001% to 0.100% as an optional element, with the balance being Zn and inevitable impurities, the total content of Fe, Mn, Co, and Cr is lower than 0.45% and the total content of Sn and Al is lower than 0.45%, a relationship of $56.0 \leq f_1 = [\text{Cu}] - 5 \times [\text{Si}] + 0.5 \times [\text{Pb}] + 0.5 \times [\text{Bi}] - 0.5 \times [\text{P}] \leq 59.5$ is satisfied, when Bi is included, a relationship of $0.003 < f_0 = [\text{Pb}] + [\text{Bi}] < 0.25$ is further satisfied, constituent phases of a metallographic structure satisfy relationships of $20 \leq (\alpha) \leq 80$, $18 \leq (\beta) \leq 80$, $0 \leq (\gamma) < 5$, $20 \times (\gamma) / (\beta) < 4$, $18 \leq (Y)^{1/2} \times 3 + (\beta) \times (-0.5 \times [\text{Si}]^{2/3} + 1.5 \times [\text{Si}]) \leq 82$, and $33 \leq (Y)^{1/2} \times 3 + (\beta) \times (-0.5 \times [\text{Si}]^{2/3} + 1.5 \times [\text{Si}]) + ([\text{Pb}] + [\text{Bi}])^{1/2} \times 38 + ([\text{P}])^{1/2} \times 15$, and a compound including P is present in β phase.

IPC 8 full level
C22C 9/04 (2006.01); **C22F 1/08** (2006.01)

CPC (source: EP KR US)
B22D 21/00 (2013.01 - US); **C22C 9/04** (2013.01 - EP KR US); **C22C 9/10** (2013.01 - US); **C22F 1/08** (2013.01 - EP KR US); **C22F 1/00** (2013.01 - EP)

Citation (search report)

- [A] EP 2775005 A1 20140910 - MITSUBISHI SHINDO KK [JP]
- [A] EP 1777305 A1 20070425 - SANBO SHINDO KOGYO KABUSHIKI K [JP]
- [A] WO 2015046421 A1 20150402 - MITSUBISHI SHINDO KK [JP]
- [A] EP 2196549 A1 20100616 - TOTO LTD [JP]
- [AD] JP 2016194123 A 20161117 - DOWA METALTECH KK
- See also references of WO 2020261636A1

Cited by
WO2024032925A1; EP4321642A1; WO2024032923A1

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

DOCDB simple family (publication)
EP 3992321 A1 20220504; EP 3992321 A4 20230809; CA 3142297 A1 20201230; CA 3142297 C 20230725; CN 113906150 A 20220107; CN 113906150 B 20230328; JP 2021042459 A 20210318; JP 6795872 B1 20201202; KR 102623143 B1 20240109; KR 20210148347 A 20211207; US 2022275479 A1 20220901; WO 2020261636 A1 20201230

DOCDB simple family (application)
EP 20831431 A 20200217; CA 3142297 A 20200217; CN 202080038596 A 20200217; JP 2020006037 W 20200217; JP 2020049928 A 20200319; KR 20217036884 A 20200217; US 202017611192 A 20200217