

Title (en)
CERMIUM-ZIRCONIUM-BASED COMPOSITE OXIDE HAVING GRADIENT ELEMENT DISTRIBUTION AND PREPARATION METHOD THEREFOR

Title (de)
CER-ZIRKONIUM-BASIERTES MISCHOXID MIT GRADIENTENELEMENTVERTEILUNG UND HERSTELLUNGSVERFAHREN DAFÜR

Title (fr)
OXYDE COMPOSITE À BASE DE CÉRIUM-ZIRCONIUM PRÉSENTANT UNE DISTRIBUTION EN GRADIENT D'ÉLÉMENTS ET PROCÉDÉ DE PRÉPARATION ASSOCIÉ

Publication
EP 4159312 A1 20230405 (EN)

Application
EP 21868422 A 20210827

Priority
• CN 202010982979 A 20200917
• CN 2021114932 W 20210827

Abstract (en)
The present invention relates to a cerium-zirconium-based composite oxide having gradient element distribution and a preparation method therefor. According to the present invention, the cerium-zirconium-based composite oxide having gradient element distribution is prepared by a step-by-step precipitation method. First, a zirconium-rich component is precipitated to form a crystal structure and a crystal grain stack structure which have high thermal stability, slow down the segregation of zirconium on a surface after high-temperature treatment, and reduce element migration among crystal grains; second, a cerium-rich component is precipitated to improve the cerium content of the surface layers of the crystal grains, improve the utilization rate of the cerium element, and improve the oxygen storage amount and the oxygen storage rate. The composite oxide prepared by the method has both high thermal stability and high oxygen storage performance, thus satisfying requirements of the long-time use of a catalyst containing a cerium-zirconium-based composite oxide for the thermal stability and oxygen storage performance of the cerium-zirconium-based composite oxide.

IPC 8 full level
B01J 23/10 (2006.01); **B01D 53/86** (2006.01); **B01D 53/94** (2006.01); **B01J 23/00** (2006.01); **F23G 7/07** (2006.01)

CPC (source: CN EP US)
B01D 53/86 (2013.01 - CN); **B01D 53/94** (2013.01 - CN); **B01D 53/945** (2013.01 - US); **B01J 21/066** (2013.01 - US); **B01J 23/002** (2013.01 - CN); **B01J 23/10** (2013.01 - CN EP US); **B01J 35/396** (2024.01 - EP); **B01J 35/613** (2024.01 - EP US); **B01J 35/633** (2024.01 - EP US); **B01J 35/635** (2024.01 - US); **B01J 35/647** (2024.01 - EP); **B01J 37/009** (2013.01 - EP US); **B01J 37/031** (2013.01 - EP); **B01J 37/038** (2013.01 - US); **B01J 37/08** (2013.01 - US); **F23G 7/07** (2013.01 - CN EP); **F23J 15/00** (2013.01 - EP); **B01D 2255/407** (2013.01 - EP US); **B01D 2255/908** (2013.01 - US); **B01D 2258/01** (2013.01 - US); **B01J 21/066** (2013.01 - EP); **F23G 2202/60** (2013.01 - EP); **F23J 2219/10** (2013.01 - EP)

Designated contracting state (EPC)
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)
BA ME

Designated validation state (EPC)
KH MA MD TN

DOCDB simple family (publication)
EP 4159312 A1 20230405; **EP 4159312 A4 20231227**; CA 3184566 A1 20220324; CN 112076740 A 20201215; JP 2023536795 A 20230830; US 2023321632 A1 20231012; WO 2022057594 A1 20220324

DOCDB simple family (application)
EP 21868422 A 20210827; CA 3184566 A 20210827; CN 202010982979 A 20200917; CN 2021114932 W 20210827; JP 2022581504 A 20210827; US 202118027044 A 20210827