

Title (en)

MG-AL MAGNESIUM ALLOY, PREPARATION METHOD FOR TUBE MADE OF MG-AL MAGNESIUM ALLOY, APPLICATION OF MG-AL MAGNESIUM ALLOY

Title (de)

MG-AL-MAGNESIUMLEGIERUNG, HERSTELLUNGSVERFAHREN FÜR ROHR AUS MG-AL-MAGNESIUMLEGIERUNG, ANWENDUNG EINER MG-AL-MAGNESIUMLEGIERUNG

Title (fr)

ALLIAGE DE MAGNÉSIUM MG-AL, PROCÉDÉ DE PRÉPARATION POUR TUBE CONSTITUÉ D'ALLIAGE DE MAGNÉSIUM MG-AL, APPLICATION D'ALLIAGE DE MAGNÉSIUM MG-AL

Publication

**EP 4279622 A1 20231122 (EN)**

Application

**EP 22739088 A 20220113**

Priority

- CN 202110040804 A 20210113
- CN 2022071812 W 20220113

Abstract (en)

The present disclosure discloses a Mg-Al based magnesium alloy, and a preparation method of a tube and an application of the same, and belongs to the technical field of alloy materials. The magnesium alloy includes, by weight percentage, 7.0-8.6% Al, 0.8-2.0% RE, 0.2-0.8% Mn, and a balance of Mg, and the magnesium alloy has an elongation of 15-22%. The preparation method of a tube of the Mg-Al based magnesium alloy includes: mixing and smelting an Al source, a RE source, a Mn source, and a Mg source to give a liquid mixed metal; casting the liquid mixed metal into a bar through semi-continuous casting; performing homogenization heat treatment on the bar at 360-400°C for 6-10h; and performing extrusion-forming on the heat-treated bar to obtain a magnesium alloy tube. The Mg-Al based magnesium alloy of the present disclosure has high elongation, and the elongation of the tube formed using the same can reach 15-22%, so that it can withstand large plastic deformation. Meanwhile, the Mg-Al based magnesium alloy has excellent welding performance and a welding loss rate of less than 6%, which greatly reduces the strength loss of magnesium alloy profiles after welding. The Mg-Al based magnesium alloy can be used in the fields of vehicle equipment and medical equipment.

IPC 8 full level

**C22C 23/02** (2006.01); **B21C 23/20** (2006.01); **C22C 1/02** (2006.01); **C22F 1/06** (2006.01)

CPC (source: CN EP KR)

**B21C 23/205** (2013.01 - CN KR); **C22C 1/02** (2013.01 - CN EP KR); **C22C 23/02** (2013.01 - CN EP KR); **C22F 1/06** (2013.01 - CN EP KR); **B21C 23/002** (2013.01 - EP); **B21C 23/205** (2013.01 - EP)

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

Designated validation state (EPC)

KH MA MD TN

DOCDB simple family (publication)

**EP 4279622 A1 20231122**; AU 2022208124 A1 20230727; CA 3205147 A1 20220721; CN 112877575 A 20210601; CN 112877575 B 20220315; CN 116761905 A 20230915; IL 304327 A 20230901; JP 2024503546 A 20240125; KR 20230131244 A 20230912; WO 2022152212 A1 20220721

DOCDB simple family (application)

**EP 22739088 A 20220113**; AU 2022208124 A 20220113; CA 3205147 A 20220113; CN 202110040804 A 20210113; CN 2022071812 W 20220113; CN 202280009957 A 20220113; IL 30432723 A 20230709; JP 2023565644 A 20220113; KR 20237027369 A 20220113