

Title (en)

ULTRAVIOLET CURABLE AQUEOUS INK COMPOSITION FOR INKJET PRINTING

Title (de)

UV-HÄRTBARE WÄSSRIGE TINTENZUSAMMENSETZUNG FÜR TINTENSTRAHLDRUCK

Title (fr)

COMPOSITION D'ENCRE AQUEUSE DURCISSABLE AUX ULTRAVIOLETS POUR IMPRESSION À JET D'ENCRE

Publication

EP 4299321 A1 20240103 (EN)

Application

EP 21928056 A 20211124

Priority

- JP 2021030998 A 20210226
- JP 2021042931 W 20211124

Abstract (en)

[origin: WO2022180962A1] The present invention addresses the problem of providing: an ultraviolet curable aqueous ink composition for inkjet printing, the ultraviolet curable aqueous ink composition exhibiting excellent compatibility and storage stability, while being capable of forming a print part, which exhibits excellent curability and water resistance without having gritty feel, by performing provisional curing after printing and subsequently performing main curing; and a printing method. The present invention provides, as a means for solving the problem, an ultraviolet curable aqueous ink composition for inkjet printing, the ultraviolet curable aqueous ink composition containing 20.0% to 70.0% by mass of a water-soluble acrylic amide monomer, 5.0% to 60.0% by mass of a water-soluble hydroxyl group-containing monofunctional monomer, and 8.0% to 35.0% by mass of a water-insoluble polymerizable compound relative to the total mass of all polymerizable components, while additionally containing a pigment, water and 3.0 to 10.0 parts by mass of a photopolymerization initiator and/or a sensitizer relative to a total of 100 parts by mass of all polymerizable components, with the ratio of the water-soluble acrylic amide monomer to the water-soluble hydroxyl group-containing monofunctional monomer (acrylic amide monomer/hydroxyl group-containing monofunctional monomer) being 0.3 to 10.0. This ultraviolet curable aqueous ink composition for inkjet printing is used for a printing process that comprises a provisional curing step which is performed by irradiation having an accumulated light quantity of 100 mJ/cm² or less by means of a UV-LED that has a peak at a wavelength of 365 nm to 405 nm.

IPC 8 full level

B41J 2/01 (2006.01); **B41M 5/00** (2006.01); **C09D 11/326** (2014.01); **C09D 11/38** (2014.01)

CPC (source: EP US)

B41J 11/00214 (2021.01 - US); **C09D 11/101** (2013.01 - EP); **C09D 11/322** (2013.01 - EP US); **C09D 11/326** (2013.01 - EP); **C09D 11/38** (2013.01 - US); **B41M 7/0081** (2013.01 - EP)

Cited by

EP4140744A4

Designated contracting state (EPC)

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

Designated extension state (EPC)

BA ME

Designated validation state (EPC)

KH MA MD TN

DOCDB simple family (publication)

EP 4299321 A1 20240103; JP 2022131834 A 20220907; US 2024132737 A1 20240425; US 2024228807 A9 20240711; WO 2022180962 A1 20220901

DOCDB simple family (application)

EP 21928056 A 20211124; JP 2021030998 A 20210226; JP 2021042931 W 20211124; US 202118547329 A 20211124